SOP FOR LABORATORY PRACTICES

HEADING/SOP NUMBER: NNV #014					
Title of Procedure: Batch Protocol for <i>NNV-BAM-Silica</i>	Revision Date: 2013-04-17				
Authors (Names):					
Kishore Natte Roberto Hanoi Labrador	Signature:				
Reviewed by: Wolfgang Unger	Signature:				

SCOPE AND APPLICABILITY

Department, Lab or Center: BAM and Nanologica AB					
Research Group: 6.6 Polymeric materials ad surfaces and Nanologica AB					
Operation/Experiment: Batch Protocol					
Material(s): Silica dispersion in H2O					

Principal Materials Used	Flammable	Causes burns	Harmful by inhalation	Irritating to eyes and respiratory system	Harmful if swallowed	Highly flammable	Contact w. combustible mat. Mav cause fire	Grades and Suppliers
Lysine				х	Х			Sigma-Aldrich
TEOS				х	Х			Sigma-Aldrich
H2O MilliQ								
MSDS attached x Yes No								

N	MATERIALS AND HAZARDS (CONT.)							
S	pecial PPE Required:							
х	Goggles							
X	Face Masks							
	Chemical Resistant Apron							

X	x Protective Clothing						
X	x Gloves						
	Butyl						
		X	Nitrile				
			PVC				
	Latex						
			Neoprene				
			Silver Shield brand				
			Kevlar				
	Other. Thermo resistant						
	Respirator (If yes, contact EHS Office for additional assistance)						

SPECIAL PRECAUTIONS

Permits: No.

Mgmt. Approval: No

Training: No

Medical Surveillance: No

Other: No

SPECIAL EMERGENCY PROCEDURES

Fire/Evacuation:	Use a fire extinguisher and active the fire alarm
Chemical Spill:	Use plenty of water to wash it
Medical Emergency:	If chemicals contact with any part of the body, wash the affected zone with plenty of water.
Personal Exposure:	No concerns if production is carried out in well-ventilated area or inside fume hood.

EQUIPMENT AND INSTRUMENTAL BY STEPS						
Steps-Operation	Equipment/Glassware	Purchased from (suggestions)				
Dissolution of lysine in H2O	Round bottom flask	Sigma-Aldrich				
	Hot plate-Stirrer	Heidolph				
Addition of TEOS	Hot plate-Stirrer	Heidolph				
	Syringe needle	Sigma-Aldrich				

Filtration	Cellulose filter	Whatman
Dialysis	Dialysis membrane	Carl Roth Gmbh

PROCEDURE									
All amounts refer to a batch synthesis in 51 ml of H2O									
Task	Hazards	Precautions	Tolerance of Step						
1. Dissolution of lysine in H2O In RBF, weigh 0.124g of lysine monohydrate and dissolve it in 51 ml of H2O. Stir it in oil bath at 60°C for 2 hours at 800 rpm. Keep RBF closed.	Acute effects in respiratory system and hands	Avoid inhalation Use gloves	Temperature: 60°C±2°C Stir Spd: 800±20rpm Time: 2±0.1h Weight: 0.124±0.001g Vol: 51±0.5ml						
2. Addition of TEOS. With a syringe+ needle add 3.9ml of TEOS. Addition under same heating-stirring conditions. Stir for 72 hours.	Acute effects in respiratory system and hands	Avoid inhalation Use gloves	Temperature: 60°C±2°C Stir Spd: 800±20rpm Time: 72±5h Vol: 3.9±0.01ml						
 Filtration Filter the silica solution with a cellulose filter Whatman 0.2μm. Take the solution with the syringe and pass it very slowly through the filter. Replace the filter once the silica solution cannot pass through. 	Acute effects in respiratory system and hands	Avoid inhalation Use gloves							
4. Dialysis Cut a portion of dialysis membrane and place it in water for 5 minutes. Close one of the edges of the wet portion and pass some air through. Add the filtered silica solution to the membrane and close the open edge. Introduce the filled membrane in to a beaker with water and stir the system for 5 days.	Acute effects hands	Use gloves	Time: 5±1min 5±0.5 days						