

Supplementary Materials

# Formaldehyde Emissions from Wooden Toys: Comparison of Different Measurement Methods and Assessment of Exposure

Morgane Even <sup>1,2,3,\*</sup>, Olaf Wilke <sup>2</sup>, Sabine Kalus <sup>2</sup>, Petra Schultes <sup>4</sup>, Christoph Hutzler <sup>1</sup> and Andreas Luch <sup>1,3</sup>

<sup>1</sup> German Federal Institute for Risk Assessment (BfR), Department of Chemical and Product Safety, Max-Dohrn-Strasse 8-10, 10589 Berlin, Germany; christoph.hutzler@bfr.bund.de (C.H.); andreas.luch@bfr.bund.de (A.L.)

<sup>2</sup> Bundesanstalt für Materialforschung und -prüfung (BAM), Division 4.2–Materials and Air Pollutants, Unter den Eichen 44-46, 12203 Berlin, Germany; olaf.wilke@bam.de (O.W.); sabine.kalus@bam.de (S.K.)


<sup>3</sup> Freie Universität Berlin, Department of Biology, Chemistry, Pharmacy, Institute of Pharmacy, Königin-Luise-Strasse 2-4, 14195 Berlin, Germany

<sup>4</sup> Chemical and Veterinary Analytical Institute Münsterland-Emscher-Lippe (CVUA-MEL), Joseph-König-Str. 40, 48147 Münster, Germany; petra.schultes@cvua-mel.de


\* Correspondence: morgane.even@bam.de




**Figure S1.** Representative pictures of the investigated toy samples.



**Figure S2.** Example image of chamber loading for sample #1 in the 1 m<sup>3</sup> chamber (a) and the microchamber (b).



**Figure S3.** Example image of chamber loading for sample #7: Pieces in the microchamber (a), pieces in the desiccator (b) and plate in the desiccator (c).



**Figure S4.** Emission profiles of formaldehyde from wooden toy pieces in the microchamber over 10 days ( $n = 2$ ; SER<sub>A</sub>, area-specific emission rate). Error bars represent standard deviation (SD).

**Table S1.** Dimensions of the samples for chamber studies; †: sample edges were partly covered; \*: approximated shape; ellipses, circles: 1<sup>st</sup> dimension are diameters.

Microchamber Samples								
No.	Geometric Shape	1st Dimension (cm)	2nd Dimension (cm)	Face Surface Area (cm <sup>2</sup> )	Perimeter (cm)	Thickness (cm)	Total Surface Sample Surface Area (cm <sup>2</sup> )	Weight (g)
#1†	parallelepiped	4.0	2.0	8.0		0.16	16.0	3.2/3.3/3.4
#2†								3.3/3.4/3.6
#3	parallelepiped	2.97	2.99	8.9		1.40	34.4	5.5/6.2
#4	cylinder	4.03		12.8		0.27	28.9	1.8/2.3
#5†	half ellipse*	4.40	2.30	8.3	8.0	0.37	19.7	1.3/1.4
#6†	triangle*	4.55	2.20	5.0	8.0	0.39	12.6	1.6
#7	2 half ellipses*	5.00 and 4.20	5.00 and 1.80	9.0	14.3	0.41	24.0	2.1
#8†	quarter circle*	5.54	86°	5.8	6.7	1.84	23.9	8.5
#9	ellipse*	4.07	3.50	11.2	13.8	0.48	29.0	8.3
#10	parallelepiped*	2.98	2.04	6.1	11.4	0.48	16.9	1.9
Dessicator Samples								
No.	Number of Pieces	Total Pieces Surface Area (cm <sup>2</sup> )		Number of Plates	Total Plates Surface Area (cm <sup>2</sup> )			
#5	16	651		1	1456			
#7	18	711		1	1426			
#8	8	828		2	1475			
1 m <sup>3</sup> Chamber Samples								
No.	Number of Plates		Total Plates Surface Area (cm <sup>2</sup> )					
#1†	2		0.93					
#2†								

**Table S2.** Flask method values of the samples similar to those studied in the microchamber and of samples after microchamber testing ( $\text{mg}/\text{kg}_{\text{toy}}$ ); usually, different pieces of the same toy sample were put together in the flask: the values reported here are the mean and standard deviation of the measurement with samples having the same characteristics (in particular color) than the samples studied in the microchambers; \*:  $\pm 30\%$  SD were estimated from experience of CVUA-MEL because there were no replicates.

No.	Similar Samples	After Microchamber (n = 1)
#1	$116 \pm 35^*$ (n = 1)	not measured
#2	$117 \pm 35^*$ (n = 1)	not measured
#3	$310 \pm 80$ (n = 2)	$346 \pm 104^*$
#4	$865 \pm 21$ (n = 2)	$365 \pm 110^*$
#5	$250 \pm 39$ (n = 4)	$309 \pm 75^*$
#6	$530 \pm 27$ (n = 3)	$561 \pm 158^*$
#7	$345 \pm 71$ (n = 2)	$286 \pm 86^*$
#8	$101 \pm 13$ (n = 3)	not measured
#9	$47 \pm 14^*$ (n = 1)	not measured
#10	$344 \pm 103^*$ (n = 1)	not measured