



Data Article

Dataset on full ultrasonic guided wavefield measurements of a CFRP plate with fully bonded and partially debonded omega stringer



Kudela Pawel^{a,*}, Radziński Maciej^a, Moix-Bonet Maria^b, Willberg Christian^b, Lugovtsova Yevgeniya^c, Bulling Jannis^c, Tschöke Kilian^d, Moll Jochen^e

^a Institute of Fluid Flow Machinery, Polish Academy of Sciences, Gdansk 80-231, Poland

^b Institute of Composite Structures and Adaptive Systems, German Aerospace Center, Braunschweig 38108, Germany

^c Federal Institute for Materials Research and Testing (BAM), Berlin 12205, Germany

^d Fraunhofer Institute for Ceramic Technologies and Systems IKTS, Systems for Condition Monitoring, Dresden 01109, Germany

^e J.W. Goethe-University, Department of Physics, Frankfurt 60438, Germany

ARTICLE INFO

Article history:

Received 5 August 2021

Revised 16 March 2022

Accepted 17 March 2022

Available online 22 March 2022

Dataset link: [Dataset on full ultrasonic guided wavefield measurements of a CFRP plate with fully bonded and partially debonded omega stringer](#)

Keywords:

Lamb waves

Composite panel

Impact damage

Damage detection

Scanning laser Doppler vibrometry

Structural Health Monitoring

Non-Destructive Evaluation

ABSTRACT

The fourth dataset dedicated to the Open Guided Waves platform [1] presented in this work aims at a carbon fiber composite plate with an additional omega stringer at constant temperature conditions. The dataset provides full ultrasonic guided wavefields. Two types of signals were used for guided wave excitation, namely chirp signal and tone-burst signal. The chirp signal had a frequency range of 20–500 kHz. The tone-burst signals had a form of sine modulated by Hann window with 5 cycles and carrier frequencies 16.5 kHz, 50 kHz, 100 kHz, 200 kHz, 300 kHz. The piezoceramic actuator used for this purpose was attached to the center of the stringer side surface of the core plate. Three scenarios are provided with this setup: (1) wavefield measurements without damage, (2) wavefield measurements with a local stringer debond and (3) wavefield measurements with a large stringer debond. The defects were caused by

* Corresponding author.

E-mail address: pk@imp.gda.pl (K. Pawel).

impacts performed from the backside of the plate. As result, the stringer feet debonds locally which was verified with conventional ultrasound measurements.

© 2022 The Author(s). Published by Elsevier Inc.
 This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/4.0/>)

Specifications Table

Subject	Mechanical Engineering
Specific subject area	Non-destructive testing, guided wave propagation, full wavefield signal processing
Type of data	Figures, matrices in hdf format
How data were acquired	Polytec PSV-400 scanning laser Doppler vibrometer;
Data format	Raw
Parameters for data collection	The planar plate dimensions were 0.5 m by 0.5 m whereas the scanning area covered almost the entire surface of the plate excluding the border about 9 mm wide. Measurements were performed in ambient temperature and humidity conditions. Various excitation signals were used, namely, Hann windowed tone-burst signal with 5 cycles and carrier frequencies 16.5 kHz, 50 kHz, 100 kHz, 200 kHz, 300 kHz and chirp signal in the frequency range 20-500 kHz.
Description of data collection	One laser head was used for registration of transverse velocities of guided wave propagation on a surface of a CFRP plate with a stringer while the excitation was performed by using a piezoelectric transducer located at the centre of the plate on the opposite side. The measurements were acquired for the intact plate and after consecutive impacts.
Data source location	Data was obtained at Institute of Fluid-Flow Machinery, Polish Academy of Sciences, Mechanics of Intelligent Structures Department, Gdansk, Poland; Impact was introduced and ultrasonic testing was performed at German Aerospace Center (DLR), Institute of Composite Structures and Adaptive Systems, Braunschweig, Germany
Data accessibility	Data is available at Zenodo platform: Data identification number: 10.5281/zenodo.5105861 Direct URL to data: https://doi.org/10.5281/zenodo.5105861

Value of the Data

- These data provide a data set for elastic guided wave inspection techniques for carbon fibre reinforced polymers with and without an introduced damage. The data thus overcomes the current limitation by a lack of freely available benchmark measurements.
- The development of new guided wave-based techniques and the comparison of existing algorithms require high-quality benchmark measurements. Therefore, all researchers in the field of non-destructive evaluation as well as in the field of guided wave-based monitoring can benefit from these data.
- The data set might be used to evaluate existing signal evaluation techniques, to enable comparisons of evaluation methods and finally to develop new signal evaluation techniques based on elastic guided wave measurements.
- Structural Health Monitoring (SHM) and non-destructive evaluation (NDE) aim to assess the integrity of a structure non-destructively. These research areas are therefore rapidly gaining in importance, and not only due to the increasing digitization of society.
- As importance of ultrasonic guided waves is also growing rapidly, new signal evaluation techniques need to be developed. The provided data set therefore makes an impact in applications ranging from aerospace and automotive to all areas of lightweight construction.

1. Data Description

The datasets within this article provide full ultrasonic guided wavefield of a CFRP plate with fully bonded (intact) and partially debonded (impacted) omega stringer measured for various excitation frequencies. The measured datasets [2] are organized as follows:

- *OGW_CFRP_Stringer_Wavefield_Intact*: Baseline wavefield measurements of the intact CFRP plate with the omega stringer.
- *OGW_CFRP_Stringer_Wavefield_FirstImpact*: Wavefield measurements of the CFRP plate with the omega stringer impacted with 15.3J at location [0.38 m, 0.33 m].
- *OGW_CFRP_Stringer_Wavefield_SecondImpact*: Wavefield measurements of the CFRP plate with the omega stringer impacted for the second time with 19J at location [0.38 m, 0.34 m].

Each folder contains a number of h5-files for two excitation types: Hann-windowed burst and chirp. The folder name for the burst excitation describes the excitation frequency and number of cycles, peak-to-peak voltage used to drive the PZT and number of averages per point used to record the wavefield, e.g. **BURST_16_5kHz_5HC_10Vpp_x3** reads as 16.5 kHz centre excitation frequency, 5 cycles Hann-windowed burst, 10V peak-to-peak and 3 averages per point. The folder name for the chirp excitation describes the excitation frequency range and chirp duration, peak-to-peak voltage used to drive the PZT and number of averages per point used to record the wavefield, e.g. **CHIRP_20-500kHz_125us_6Vpp_x3** reads as 20–500 kHz excitation frequency range, 125 μ s chirp duration, 6V peak-to-peak and 3 averages per point. It should be noted that these descriptions correspond to signals coming from a signal generator which were next amplified 20 times by a high voltage amplifier.

To open a h5-file and to see how the h5-files are organized the following options are available:

- HDFView <https://support.hdfgroup.org/products/java/hdfview/>
- HDF Compass <https://github.com/HDFGroup/hdf-compass>
- a MATLAB command *h5disp*


In addition, MATLAB and Python scripts are included which can be used to read out the dataset and to visualise the wavefield.

2. Experimental Design, Materials and Methods


2.1. Description of composite panel

The CFRP plate corresponds to the *wave field* plate in [3]. It was manufactured with a dimension of 0.5 m \times 0.5 m and a nominal thickness of 2 mm. The corresponding ply thickness is 0.125 mm. The prepreg M21 / 34% / UD134 / T700 / 300 from Hexply® was used to manufacture the plates with a quasi-isotropic (QI) layup of [45/0/–45/90/–45/0/45/90]_S. The material properties of a single unidirectional layer were measured based on standard test procedures [1]. The prepreg M21 / 34% / UD194 / T700 / IMA-12K from Hexply® was used to separately manufacture the omega stringer. The stringer was built also in a quasi-isotropic layup [–45/0/90/45/90/–45]_S with the dimensions depicted in Fig. 1. The nominal thickness is 1.5 mm with a ply thickness of 0.125 mm. The material properties of plate and stringer are listed in Table 1. The omega stringer was bonded to the plate by using Loctite Hysol 9466. The adhesive was cured in vacuum at room temperature.

A mobile impactor from ID-Lindner has been used to create Barely Visible Impact Damages (BVID) in the specimen. The mobile impactor generates an impact with a defined energy by shooting a metal projectile by means of compressed air. A hemi-spherical projectile with a radius of 25 mm has been employed in order to create BVID. Two impacts have been carried out. The first was executed with an energy of 15.3J and a speed of 6 m s^{–1} on the coordinates $x = 0.38$ m



(a) Specimen dimensions and measurement area denoted by grey colour.



(b) Omega stringer cross-section geometry in mm, taken from [3].

Fig. 1. Plate with omega stringer geometry.

Table 1

Stiffness values and density for unidirectional M21 / 34% / UD134 / T700 / 300 material used for the plate, taken from Moll et al. [1], and M21 / 34% / UD194 / IMA-12K as material used for the stringer.

Parameter	M21 / 34% / UD134 / T700 / 300	M21 / 34% / UD194 / IMA-12K
C_{1111} [GPa]	130	174
C_{1122} [GPa]	6.1	4.1
C_{1133} [GPa]	6.1	4.1
C_{2222} [GPa]	11.2	9.6
C_{2233} [GPa]	5.2	2.9
C_{3333} [GPa]	11.2	9.6
C_{1212} [GPa]	3	3.3
C_{2323} [GPa]	4.2	5.9
C_{1313} [GPa]	4.2	5.9
ρ [kgm^{-3}]	1571	1580

and $y = 0.33$ m according to Fig. 1a. During the second impact the projectile had a speed of 6.7 ms^{-1} and the impact energy of 19J. The second impact was located 10 mm above the first impact position, with the intention of increasing the damage size.

2.2. Ultrasound NDT measurements

As a reference, non-destructive inspection (NDI) was carried out with the ultrasound equipment USPC 4000 AirTech, from Hillger. Fig. 2 displays the C-Scans made after each impact. The colour coding indicates the time-of-flight of the back-wall echo. As observed in Fig. 2a, the first impact created a minimal debonding between skin and stringer with dimensions around $12 \times 50 \text{ mm}$. After the second impact the debonding grew considerably, affecting both feet of the omega stringer. The large extent of the second impact, with damaged areas far from the impact location, can be explained by the mechanical properties of the specimen. The impact induces a bending load in the specimen. Due to the stiffness of the stringer, the bending load generates large shear forces in the bonded joint. The adhesive layer, probably weakened from the first impact, did not withstand the shear forces during the second impact. The final damage on the specimen is displayed on Fig. 2b.

2.3. Data acquisition using scanning laser Doppler vibrometry


Guided waves were excited by a piezoelectric disk of diameter 10 mm attached to the back surface of the specimen (the side with omega stringer). The following excitation signals were applied in consecutive measurements:

- Hann windowed tone-burst signal with 5 cycles and carrier frequencies (f_c) 16.5 kHz, 50 kHz, 100 kHz, 200 kHz, 300 kHz,
- chirp signal in the frequency range 20–500 kHz lasting 200 μs .


The excitation signals used in this paper are illustrated both in the time and frequency domains in Figs. 3–8.

The applied peak to peak voltage at the signal generator varied depending on the type of the signal from 4V to 11V. Next, signals were amplified 20 times.

The measurements using scanning laser Doppler vibrometer (SLDV) were conducted on the opposite side of the specimen in respect to the piezoelectric transducer and omega stringer (on the flat surface). The specimen central area excluding border of width about 9 mm was measured in 483×483 points. The specimen with highlighted measurement area is presented in Fig. 1a. At every measurement point, 1024 time samples were registered for Hann windowed signals and 2048 time samples for chirp signals. The sampling frequency for burst excitation



(a) C-Scan after first impact with arrow indicating the impact position



(b) C-Scan after second impact with arrow indicating the impact position

Fig. 2. Ultrasound C-scans after impacts with back-wall echo time-of-flight.




Fig. 3. The tone-burst excitation signal for the carrier frequency $f_c = 16.5$ kHz.




Fig. 4. The tone-burst excitation signal for the carrier frequency $f_c = 50$ kHz.




Fig. 5. The tone-burst excitation signal for the carrier frequency $f_c = 100$ kHz.




Fig. 6. The tone-burst excitation signal for the carrier frequency $f_c = 200$ kHz.

measurements was in range of 256 kHz up to 2.56 MHz chosen from series to be around 10 times higher than f_c . The sampling frequency for chirp excitation was 1.28 MHz.

The measurements were taken 10 times in every grid point and averaged to improve the signal to noise ratio. The exception was the case of Hann windowed tone-burst signal of carrier frequency 16.5 kHz where only 3 averages were applied. The origin of the coordinate system is located in the lower-left corner of the specimen.

It should be noted that the dataset contains raw signals, however, a band-pass filter embedded in the Polytec data acquisition system was used during measurements. The band-pass cut off frequencies were $f_{cut1} = 0.5f_c$ and $f_{cut2} = 1.5f_c$.




Fig. 7. The tone-burst excitation signal for the carrier frequency $f_c = 300$ kHz.




Fig. 8. The chirp excitation signal.

2.4. *Wavefield animation*

Full wavefields of guided waves measured by the scanning laser Doppler vibrometer are of great importance in the field of SHM and NDE. They can be used for validation of various numerical models [4,5] as well as for development of damage identification algorithms [6–10]. Hence, our aim is to provide such a dataset so that various methods can be quantitatively compared.

The dataset is accompanied by Matlab script `Read_AcousticWavefield.m` as well as Python scripts `readData.py` and `makeVideo.py` which can be used for reading and visualising data. The scripts should be copied to the desired sub-folder with *.h5 files so that data will be processed in the current path or alternatively scripts can be modified by including full paths.

Exemplary frames of propagating waves for the case of 100 kHz excitation are presented in Fig. 9. Three cases are presented: (i) intact specimen (Fig. 9a and b), (ii) specimen after first impact (Fig. 9c and d) and (iii) specimen after second impact. It can be noted that slight differences in the wave pattern caused by the impact appear at 0.15 ms in Fig. 9d. In Fig. 9e reflection from the stringer is not present which means that the stringer foot debonded from the plate.

2.5. *Postprocessing*

A simple postprocessing was applied to the acquired full wavefield measurements. The goal is to show that partial debonding of the stringer from the host plate is a challenging problem. Simple signal processing method such as weighted root mean square (WRMS) [6] is not able




Fig. 9. Exemplary frames of propagating waves for the case of intact plate, first impact and second impact.




Fig. 10. WRMS showing energy distribution for the case of intact plate, first impact and second impact.

to highlight the defected area. Only slight changes in the energy distribution are visible as it is presented in Fig. 10. Therefore, more advanced signal processing algorithms must be developed and the provided dataset can serve as a benchmark. On the other hand, after second impact, stringer has partially debonded from the plate. Based on WRMS image in Fig. 10c it can be concluded that the debonding is extensive - only upper right part of the foot of the stringer remains in contact with the plate.

Another post-processing technique used in this work is a local wavenumber mapping technique introduced by Rogge and Leckey [7] in combination with the one-frequency-approach of Mesnil et al. [8]. Wavenumber mapping allows to identify discontinuities in wavenumbers which are caused by local changes in thickness. For instance, a wave travelling in a pristine composite plate will have a different wavenumber than that of a delaminated region. The wavenumber in the damaged region will be equal to that of the plate portion above/below the delamination, when measurement are done on top/bottom.

The necessary steps along with the source code to calculate the wavenumber maps can be found in [9]. The A0-like mode only was used for the analysis due to its sensitivity to the thickness variation. All other modes were filtered out by applying a radial filter in the wavenumber domain leaving the wavenumbers between 350 rad m^{-1} and 750 rad m^{-1} only. The point-




Fig. 11. Local wavenumber maps at 100 kHz calculated from the wavefield measurements at the same excitation frequency. A black dot marks the position of the impact.

wise window size of 31×31 bins was applied which corresponds to 31 mm and fulfills the wavenumber resolution criteria of the window size being at least two wavelengths of the expected modes [7]. Moreover, the wavenumber maps were filtered using a median filter of 11×11 bins to reduce the influence of the measurement noise and artefacts. Calculations were done in MATLAB on a 64-bit Windows 10 PC with 32 GB RAM for a wavefield data set which was zero-padded in space to the size of $512 - 512 \times 1024$. The computational time for one wavenumber map was about 18 m.

First of all, the transducer is visible in every wavenumber map in the middle of sample having the wavenumber of 520 rad m^{-1} . A typical edge artifact can be observed too. The feet of the stringer are highlighted at positions around $y = 0.33 \text{ m}$ and $y = 0.42 \text{ m}$ with the wavenumber of $\approx 500 \text{ rad m}^{-1}$. Note that the wavenumber for the upper foot are not homogeneous through its length which may indicate the lack of bonding at the discontinuities, e.g. see a region at $y = 0.42 \text{ m}$ and $x = 0.18 - 0.24 \text{ m}$ in Fig. 11a and 11b. These discontinuities are also partially visible in WRMS maps shown in Fig. 10a and b. Moreover, the anisotropy of the composite plate becomes apparent in the wavenumber maps, especially for the case of the second impact shown in Fig. 11c. The left upper as well as the right bottom quadrants of the map have wavenumbers around 610 rad m^{-1} , whereas the left bottom and right upper quadrants have wavenumbers around 560 rad m^{-1} .

As for the impact damage, the first impact caused only a small delamination in the structure which is hardly recognisable in the wavenumber map, confer Fig. 11a and b. A black dot in Fig. 11b marks the impact position. The change in the wavenumber between intact structure

and the structure after the first impact varies between 5 rad m^{-1} and 29 rad m^{-1} , measured to the right of the impact location at positions $y = 0.33 \text{ m}$ and $x = 0.415 \text{ m}$, and $y = 0.33 \text{ m}$ and $x = 0.418 \text{ m}$, respectively. This damage would probably go unnoticed, if one would not know where to look at. The WRMS map shown in Fig. 10b gives a better indication of the damage thanks to the scattering of the waves at the delamination. For the case of the second impact, both WRMS (Fig. 10c) and wavenumber (Fig. 11c) maps indicated the debonding of the whole bottom foot and the left half of the upper foot. All in all, for the case presented here, the only difference of wavenumber mapping over WRMS is additional information provided about the plate's anisotropy.

Declaration of Competing Interest

The authors declare that they have no known competing financial interests or personal relationships which have, or could be perceived to have, influenced the work reported in this article.

Data Availability

[Dataset on full ultrasonic guided wavefield measurements of a CFRP plate with fully bonded and partially debonded omega stringer.](#)

CRediT Author Statement

Kudela Pawel: Funding acquisition, Supervision, Project administration, Software, Visualization, Data curation, Writing – original draft, Writing – review & editing; **Radzienski Maciej:** Investigation, Validation, Writing – original draft, Writing – review & editing; **Moix-Bonet Maria:** Investigation, Visualization, Data curation, Writing – original draft, Writing – review & editing; **Willberg Christian:** Software, Validation, Writing – original draft, Writing – review & editing; **Lugovtsova Yevgeniya:** Investigation, Visualization, Writing – original draft, Writing – review & editing; **Bulling Jannis:** Funding acquisition, Investigation, Data curation, Writing – original draft, Writing – review & editing; **Tschöke Kilian:** Investigation, Data curation, Writing – original draft, Writing – review & editing; **Moll Jochen:** Conceptualization, Supervision, Methodology, Writing – original draft, Writing – review & editing.

Acknowledgments

Pawel Kudela would like to thank the Polish National Science Center for the finance support under grant agreement no. 2018/31/B/ST8/00454. Jannis Bulling gratefully acknowledges the German Research Foundation for funding (DFG project number 428590437).

References

- [1] J. Moll, J. Kathol, C.-P. Fritzen, M. Moix-Bonet, M. Rennoch, M. Koerd, A.S. Herrmann, M.G.R. Sause, M. Bach, Open guided waves - online platform for ultrasonic guided wave measurements, *Struct. Health Monit.* 18 (5–6) (2019) 1903–1914, doi:[10.1177/1475921718817169](https://doi.org/10.1177/1475921718817169).
- [2] P. Kudela, M. Radzienski, M. Moix-Bonet, C. Willberg, Y. Lugovtsova, J. Bulling, K. Tschöke, J. Moll, Dataset on full ultrasonic guided wavefield measurements of a CFRP plate with fully bonded and partially debonded omega stringer (1.0) [data set], Zenodo (2021), doi:[10.5281/zenodo.5105861](https://doi.org/10.5281/zenodo.5105861).
- [3] J. Moll, C. Kexel, J. Kathol, C.-P. Fritzen, M. Moix-Bonet, C. Willberg, M. Rennoch, M. Koerd, A. Herrmann, Guided waves for damage detection in complex composite structures: the influence of omega stringer and different reference damage size, *Appl. Sci.* 10 (9) (2020), doi:[10.3390/app10093068](https://doi.org/10.3390/app10093068).
- [4] Y. Shen, C.E. Cesnik, Hybrid local FEM/global LISA modeling of damped guided wave propagation in complex composite structures, *Smart Mater. Struct.* 25 (9) (2016), doi:[10.1088/0964-1726/25/9/095021](https://doi.org/10.1088/0964-1726/25/9/095021).

- [5] P. Kudela, J. Moll, P. Fiborek, Parallel spectral element method for guided wave based structural health monitoring, *Smart Mater. Struct.* 29 (9) (2020) 095010, doi:[10.1088/1361-665X/ab9e10](https://doi.org/10.1088/1361-665X/ab9e10).
- [6] M. Radzieński, Ł. Doliński, M. Krawczuk, A. Żak, W. Ostachowicz, Application of RMS for damage detection by guided elastic waves, *J. Phys.* 305 (2011) 012085, doi:[10.1088/1742-6596/305/1/012085](https://doi.org/10.1088/1742-6596/305/1/012085).
- [7] M.D. Rogge, C.A. Leckey, Characterization of impact damage in composite laminates using guided wavefield imaging and local wavenumber domain analysis, *Ultrasonics* 53 (7) (2013) 1217–1226, doi:[10.1016/j.ultras.2012.12.015](https://doi.org/10.1016/j.ultras.2012.12.015).
- [8] O. Mesnil, C.A. Leckey, M. Ruzzene, Instantaneous and local wavenumber estimations for damage quantification in composites, *Struct. Health Monit.* 14 (3) (2015) 193–204, doi:[10.1177/1475921714560073](https://doi.org/10.1177/1475921714560073).
- [9] Y. Lugovtsova, J. Bulling, O. Mesnil, J. Prager, D. Gohlke, C. Boller, Damage quantification in an aluminium-cfrp composite structure using guided wave wavenumber mapping: comparison of instantaneous and local wavenumber analyses, *NDT & E Int.* 122 (2021) 102472, doi:[10.1016/j.ndteint.2021.102472](https://doi.org/10.1016/j.ndteint.2021.102472).
- [10] W.J. Staszewski, R.B. Jenal, A. Klepka, M. Szewedo, T. Uhl, A review of laser doppler vibrometry for structural health monitoring applications, *Key Eng. Mater.* 518 (2012) 1–15, doi:[10.4028/KEM.518.1](https://doi.org/10.4028/KEM.518.1).