



Supporting Information

for

Laser-processed antiadhesive bionic combs for handling nanofibers inspired by nanostructures on the legs of cribellate spiders

Sebastian Lifka, Kristóf Harsányi, Erich Baumgartner, Lukas Pichler, Dariya Baiko, Karsten Wasmuth, Johannes Heitz, Marco Meyer, Anna-Christin Joel, Jörn Bonse and Werner Baumgartner

Beilstein J. Nanotechnol. **2022**, *13*, 1268–1283. doi:10.3762/bjnano.13.105

Additional experimental data

Table S1: Morphological data of the nanoripples found on the calamistrum of four distantly related cibellate spiders.

Species	Periodicity (nm)	Height (nm)
<i>Amaurobius similis</i>	222 ± 8 (n = 3)	210 (n = 1)
<i>Hickmania troglodytes</i>	205 ± 13 (n = 3)	
<i>Jamberoo johnnoblei</i>	233 (n = 1)	
<i>Uloborus plumipes</i>	216 ± 10 (n = 3)	200 ^a

^aData taken from [1].

Table S2: Statistical analysis of the presented measurement results (Two-tail *t*-test assuming equal variances, confidence level 95%).

Sample 1	Sample 2	P value	Statistically significant
Al alloy polished	Al alloy LIPSS	0.91	No
Steel polished	Steel LIPSS	8.85e-7	Yes
Ti alloy polished	Ti alloy LIPSS	3.14e-4	Yes
Ti alloy faced	Ti alloy LIPSS	2.49e-5	Yes
Ti alloy 240	Ti alloy LIPSS	6.66e-5	Yes
Ti alloy 80	Ti alloy LIPSS	4.76e-7	Yes
Ti alloy faced	Ti alloy polished	0.25	No
Ti alloy 240	Ti alloy polished	0.01	Yes
Ti alloy 80	Ti alloy polished	8.09e-4	Yes




Figure S1: Scanning electron micrographs of the surface of the investigated samples.
(a) Al alloy LIPSS-covered; (b) steel LIPSS-covered; (c) Ti alloy LIPSS-covered; (d) Ti alloy faced; (e) Ti alloy 240; (f) Ti alloy 80.

References

1. Joel, A.-C.; Meyer, M.; Heitz, J.; Heiss, A.; Park, D.; Adamova, H.; Baumgartner, W. *ACS Appl. Nano Mater.* **2020**, 3, 3395–3401.

doi.org/10.1021/acsanm.0c00130