

Table S.7a

Relative frequency of the particle number in dependence of the gravimetric particle diameter.

D_i / μm	0.010	0.022	0.041	0.072	0.122	0.200	0.314	0.482	0.759	1.250	2.017	3.017	4.448	7.312
PA_FR / %	0.0 ±	2.5 ±	11.5 ±	18.6 ±	21.3 ±	15.4 ±	14.6 ±	10.3 ±	4.1 ±	1.2 ±	0.3 ±	0.1 ±	0.0 ±	0.0 ±
	0.1	2.3	7.4	11.7	13.5	9.1	8.3	5.9	2.3	0.7	0.2	0.1	0.1	0.1
PA_ZnSt_1 / %	0.0 ±	3.8 ±	13.3 ±	16.8 ±	18.9 ±	15.3 ±	14.6 ±	10.9 ±	4.6 ±	1.3 ± 1	0.3 ±	0.1 ±	0.0 ±	0.0 ±
	0.1	5.4	11.4	13.5	13.3	10.4	10.4	7.6	3.4		0.2	0.1	0.1	0.1
PA_ZnSt_5 / %	11.8 ±	6.8 ±	17.8 ±	16.4 ±	16.8 ±	11.4 ±	10.0 ±	6.2 ±	2.1 ±	0.5 ±	0.1 ±	0.1 ±	0.0 ±	0.0 ±
	16.1	6.1	1.6	3.6	4.2	2.9	2.6	1.5	0.5	0.1	0.1	0.1	0.1	0.1
PA_ZnP / %	8.0 ±	3.3 ±	12.5 ±	16.0 ±	18.1 ±	15.2 ±	13.1 ±	9.0 ±	3.5 ±	1.0 ±	0.2 ±	0.1 ±	0.0 ±	0.0 ±
	13.9	3.9	3.1	5.6	6.4	4.7	4.1	2.7	0.9	0.2	0.1	0.1	0.1	0.1
PA_TiO2 / %	0.0 ±	1.0 ±	10.4 ±	14.1 ±	23.5 ±	17.9 ±	15.6 ±	11.3 ±	4.4 ±	1.3 ±	0.3 ±	0.1 ±	0.0 ±	0.0 ±
	0.1	1.4	14.4	11.2	9.2	6.2	6.7	4.5	1.5	0.4	0.1	0.1	0.1	0.1
PA_HT / %	0.0 ±	0.0 ±	0.6 ±	14.3 ±	32.2 ±	21.4 ±	17.3 ±	10.2 ±	3.2 ±	0.6 ±	0.1 ±	0.1 ±	0.0 ±	0.0 ±
	0.1	0.1	0.4	0.8	1.2	0.9	1.3	1.2	0.7	0.2	0.1	0.1	0.1	0.1

Table S.7b

Relative frequency of the particle mass in dependence of the gravimetric particle diameter.

D_i / μm	0.010	0.022	0.041	0.072	0.122	0.200	0.314	0.482	0.759	1.250	2.017	3.017	4.448	7.312
PA_FR / %	0.0 ±	0.0 ±	0.0 ±	0.0 ±	0.2 ±	0.6 ±	2.1 ±	5.2 ±	8.1 ±	10.6 ±	12.0 ±	9.7 ±	16.3 ±	35.2 ±
	0.1	0.1	0.1	0.1	0.1	0.3	1.2	3.0	4.6	6.4	8.7	8.6	16.9	43.1
PA_ZnSt_1 / %	0.0 ±	0.0 ±	0.0 ±	0.0 ±	0.2 ±	0.7 ±	2.6 ±	6.9 ±	11.3 ±	14.9 ±	15.1 ±	10.1 ±	13.8 ±	24.3 ±
	0.1	0.1	0.1	0.1	0.1	0.5	1.8	4.8	8.5	11.4	11.6	6.3	8.6	16.7
PA_ZnSt_5 / %	0.0 ±	0.0 ±	0.0 ±	0.1 ±	0.5 ±	1.5 ±	5.2 ±	11.6 ±	15.7 ±	17 ±	14.7 ±	7.5 ±	10.9 ±	15.4 ±
	0.1	0.1	0.1	0.1	0.2	0.6	2.2	4.6	6.2	6.0	5.1	5.6	16.7	34.3
PA_ZnP / %	0.0 ±	0.0 ±	0.0 ±	0.0 ±	0.3 ±	0.9 ±	3.2 ±	7.8 ±	11.8 ±	15.1 ±	15.8 ±	11.1 ±	14.2 ±	19.7 ±
	0.1	0.1	0.1	0.1	0.1	0.3	1.0	2.3	3.0	2.9	1.1	1.3	4.0	9.7
PA_TiO2 / %	0.0 ±	0.0 ±	0.0 ±	0.0 ±	0.2 ±	0.8 ±	2.5 ±	6.6 ±	10.2 ±	13.1 ±	13.3 ±	9.5 ±	15.4 ±	28.2 ±
	0.1	0.1	0.1	0.1	0.1	0.3	1.1	2.7	3.6	3.8	2.1	0.1	0.6	3.6
PA_HT / %	0.0 ±	0.0 ±	0.0 ±	0.0 ±	0.4 ±	1.1 ±	3.4 ±	7.2 ±	8.7 ±	7.1 ±	7.4 ±	10.2 ±	20.1 ±	34.5 ±
	0.1	0.1	0.1	0.1	0.1	0.1	0.2	0.9	1.8	2.3	1.5	0.6	0.3	2.1