

Weierstraß-Institut für Angewandte Analysis und Stochastik

im Forschungsverbund Berlin e.V.

Preprint

ISSN 0946 – 8633

Thermally driven phase transformation in shape-memory alloys

Alexander Mielke ^{1,2}, Adrien Petrov ¹

submitted: 20th September 2007

¹ Weierstraß-Institut
für Angewandte Analysis und Stochastik
Mohrenstraße 39
10117 Berlin, Germany
E-Mail: mielke@wias-berlin.de
E-Mail: petrov@wias-berlin.de

² Institut für Mathematik
Humboldt-Universität zu Berlin
Rudower Chaussee 25
12489 Berlin, Germany

No. 1257

Berlin 2007



2000 *Mathematics Subject Classification.* 49J40, 74C05, 74F05, 74M05, 74N30.

Key words and phrases. shape-memory materials, temperature-induced phase transformation, rate-independent processes, energetic formulation, doubly nonlinear differential inclusion.

A.P. was supported by the Deutsche Forschungsgemeinschaft within the project C18 “Analysis and numerics of multidimensional models for elastic phase transformation in a shape-memory alloys” of the DFG Research Center MATHEON.

Edited by
Weierstraß-Institut für Angewandte Analysis und Stochastik (WIAS)
Mohrenstraße 39
10117 Berlin
Germany

Fax: + 49 30 2044975
E-Mail: preprint@wias-berlin.de
World Wide Web: <http://www.wias-berlin.de/>

Abstract

This paper analyzes a model for phase transformation in shape-memory alloys induced by temperature changes and by mechanical loading. We assume that the temperature is prescribed and formulate the problem within the framework of the energetic theory of rate-independent processes. Existence and uniqueness results are proved.

1 Introduction

Shape-memory alloys (SMA) have some surprising thermo-mechanical behavior; one can observe that severely deformed alloys recover their original shape after a thermal cycle (*shape-memory effect*). The exploitation in innovative and commercially valuable applications stimulates the interest in the development of mathematical models for shape-memory materials. Many underlying one-dimensional models are available in the literature but multi-dimensional models allowing for multiaxial loadings and anisotropies are rare. For the isothermal setting such models are discussed in [MTL02, GMH02, KMR05].

In this paper, we are concerned with quasi-static evolution of shape-memory materials in a small-strain regime under non-isothermal conditions. More precisely, we study a macroscopic phenomenological model for shape-memory polycrystalline materials undergoing phase transformation driven by stress or temperature changes. This model was originally proposed by Souza et al. [SMZ98] and later addressed and extended by Auricchio et al. [AuP02, AuP04, AMS07]. We follow the mathematical study of a temperature-driven phase transformation as proposed by Mielke in [Mie07].

The temperature θ is given *a priori* as an applied load and we write $\theta = \theta_{\text{appl}}(t, x)$. This assumption is used in engineering models and it is acceptable if the body is small in at least one direction. Then, the excessive or missing heat can be balanced through the environment.

Our model is described by a stored-energy density $W(e, z, \theta_{\text{appl}})$, where $e = e(u) = \frac{1}{2}(\nabla u + \nabla u^T)$ and z is a macroscopic internal variable keeping track of the phase distribution. The potential energy takes the following form

$$\mathcal{E}(t, u, z) \stackrel{\text{def}}{=} \int_{\Omega} W(e(u), z, \theta_{\text{appl}}(t, \cdot)) + \frac{\sigma}{2} |\nabla z|^2 \, dx - \langle l(t), u \rangle, \quad \sigma > 0,$$

where l denotes the time-dependent applied loading. Moreover we specify the dissipation potential by

$$\mathcal{R}(\dot{z}) \stackrel{\text{def}}{=} \int_{\Omega} \rho |\dot{z}| \, dx = \rho \|\dot{z}\|_{L^1(\Omega)}, \quad \rho > 0,$$

where $z \in \mathcal{Z} \stackrel{\text{def}}{=} W^{1,2}(\Omega)$. The set \mathcal{F} of admissible displacements is specified as those functions $u \in W^{1,2}(\Omega)$ satisfying the Dirichlet data at the part $\Gamma_{\text{Dir}} \subset \partial\Omega$. Then, our problem can be posed like the *energetic formulation* for rate-independent problems. For a given initial value $(u(0), z(0)) = (u_0, z_0) \in \mathcal{F} \times \mathcal{Z}$, we have to find a function $(u, z) : [0, T] \rightarrow \mathcal{F} \times \mathcal{Z}$ such that for all $t \in [0, T]$, the *global stability condition* (S) and the *global energy conservation* (E) are satisfied, i.e.

$$(S) \quad \forall (u, z) \in \mathcal{F} \times \mathcal{Z} : \mathcal{E}(t, u(t), z(t)) \leq \mathcal{E}(t, \bar{u}, \bar{z}) + \mathcal{R}(\bar{z} - z(t)),$$

$$(E) \quad \mathcal{E}(t, u(t), z(t)) + \int_0^t \mathcal{R}(\dot{z}(s)) \, ds = \mathcal{E}(0, u_0, z_0) + \int_0^t \partial_s \mathcal{E}(s, u(s), z(s)) \, ds.$$

The paper is organized as follows. In Section 2, the mathematical formulation of the problem within the framework of the energetic theory of rate-independent processes is presented. In Section 3, we specify the exact assumptions, and then some helpful estimates on the constitutive function W are obtained. These estimates imply that the partial derivative $\partial_t \mathcal{E}(t, u, z)$ is defined whenever $\mathcal{E}(t, u, z) < \infty$. Then, with standard arguments we show that for all stable initial data (u_0, z_0) an energetic solution exists. Finally, in Section 6 using uniform convexity of $\mathcal{E}(t, \cdot, \cdot)$ and the temporal smoothness of solutions obtained in Section 5, we prove the uniqueness result. The model discussed here is much simpler than the ones treated in [CHM02, BC*04, KMR05], since it is essentially restricted to isotropic behavior in polycrystals. However, this allows us to go much further in the mathematical analysis. For the more elaborate models only existence result are known, while here we are able to derive Lipschitz dependence of the solutions on the initial data.

2 Mathematical formulation

We consider a body with reference configuration $\Omega \subset \mathbb{R}^d$. This body may undergo phase transformation and elastic displacements $u : \Omega \rightarrow \mathbb{R}^d$. The phase transformation will be characterized by the internal variable $z : \Omega \rightarrow \mathbb{R}_{\text{dev}}^{d \times d}$ denoting the mesoscopic transformation strain where $\mathbb{R}_{\text{dev}}^{d \times d}$ is the space of symmetric $d \times d$ tensors with vanishing trace. We will denote by $\mathbb{R}_{\text{sym}}^{d \times d}$ the space of symmetric $d \times d$ tensors endowed with the scalar product $v:w \stackrel{\text{def}}{=} \text{tr}(v^T w)$ and the corresponding norm is given by $|v|^2 \stackrel{\text{def}}{=} v:v$ for all $v, w \in \mathbb{R}_{\text{sym}}^{d \times d}$. Here $(\cdot)^T$ and $\text{tr}(\cdot)$ denote the transpose and the trace of the matrix (\cdot) , respectively.

The set of admissible displacements $\mathcal{F} \stackrel{\text{def}}{=} \{u \in W^{1,2}(\Omega; \mathbb{R}^d) \mid u|_{\Gamma_{\text{Dir}}} = 0\}$ is chosen as a suitable subspace of $W^{1,2}(\Omega; \mathbb{R}^d)$ by describing Dirichlet data at the part Γ_{Dir} of

$\partial\Omega$. The internal variable z lies in $\mathcal{Z} = W^{1,2}(\Omega; \mathbb{R}^{d \times d})$. We will denote the states by $q \stackrel{\text{def}}{=} (u, z)$ and the norm and the scalar product in $\mathcal{Q} \stackrel{\text{def}}{=} \mathcal{F} \times \mathcal{Z}$ by $\|\cdot\|_{\mathcal{Q}}$ and $\langle \cdot, \cdot \rangle_{\mathcal{Q}}$, respectively.

The material behavior will depend on the temperature θ , which will be considered as a time dependent given parameter. Hence, we will not solve an associated heat equation, but we will treat θ as an applied load and denote it by $\theta_{\text{appl}} : [0, T] \times \Omega \rightarrow [\theta_{\min}, \theta_{\max}]$. This approximation for the temperature is used in engineering models and we may justify it in the case where the changes of the loading are slow and the body is small in at least one direction such that excess of heat can be transported very fast to the surface and then radiated into the environment.

The linearized strain tensor $e = e(u)$ is given by $e(u) \stackrel{\text{def}}{=} \frac{1}{2}(\nabla u + \nabla u^\top) \in \mathbb{R}^{d \times d}$. We assume that Ω is such that there exists $c_\Omega > 0$ such that Korn's inequality holds, i.e.

$$v \in W^{1,2}(\Omega; \mathbb{R}^d) : c_\Omega \|v\|_{W^{1,2}}^2 \leq \|v\|_{L^2}^2 + \|e(v)\|_{L^2}^2.$$

Moreover, $\Gamma_{\text{Dir}} \subset \partial\Omega$ is assumed to be big enough such that there exists $c_{\text{Korn}} > 0$ with

$$\forall u \in \mathcal{F} : \|e(u)\|_{L^2}^2 \geq c_{\text{Korn}} \|u\|_{W^{1,2}}^2. \quad (2.1)$$

For more details on Korn's inequality and its consequences, we refer to [DuL76].

The potential energy takes then the following form

$$\widehat{\mathcal{E}}(t, q, \theta) \stackrel{\text{def}}{=} \int_{\Omega} W(e(u), z, \theta) + \frac{\sigma}{2} |\nabla z|^2 \, dx - \langle l(t), u \rangle, \quad (2.2)$$

where $W : \mathbb{R}_{\text{sym}}^{d \times d} \times \mathbb{R}_{\text{dev}}^{d \times d} \times [\theta_{\min}, \theta_{\max}] \rightarrow \mathbb{R}$ takes the form

$$W(e(u), z, \theta) \stackrel{\text{def}}{=} \frac{1}{2}(e(u) - z) : \mathbb{C}(\theta) : (e(u) - z) + h(z, \theta)$$

with $h(\cdot, \theta) : \mathbb{R}_{\text{dev}}^{d \times d} \rightarrow \mathbb{R}$ convex. Here σ is a positive coefficient that measures some nonlocal interaction effect for the internal variable z , $\mathbb{C}(\theta)$ is the elasticity tensor which depends on the temperature θ , and $l(t)$ denotes the applied mechanical loading in the form

$$\langle l(t), u \rangle \stackrel{\text{def}}{=} \int_{\Omega} f_{\text{appl}}(t, x) \cdot u(x) \, dx + \int_{\partial\Omega} g_{\text{appl}}(t, x) \cdot u(x) \, d\gamma.$$

Since θ is given we denote the potential energy by $\mathcal{E}(t, q) \stackrel{\text{def}}{=} \widehat{\mathcal{E}}(t, q, \theta_{\text{appl}}(t))$.

The dissipation potential is defined by

$$\mathcal{R}(\dot{z}) \stackrel{\text{def}}{=} \int_{\Omega} \rho |\dot{z}| \, dx = \rho \|\dot{z}\|_{L^1(\Omega)}, \quad \rho > 0. \quad (2.3)$$

As usual, the notation $(\dot{\cdot})$ denotes the time derivative $\frac{d}{dt}$. One can prove that $\mathcal{R} : \mathcal{Z} \rightarrow \mathbb{R}$ is convex, lower semicontinuous and positively homogeneous of degree 1, i.e. for all $\gamma \geq 0$ and $v \in \mathcal{Z}$, $\mathcal{R}(\gamma v) = \gamma \mathcal{R}(v)$. Its subdifferential is defined by

$$\partial\mathcal{R}(v) = \left\{ \sigma \in \mathcal{Z}^* \mid \forall w \in \mathcal{Z} : \mathcal{R}(w) \geq \mathcal{R}(v) + \int_{\Omega} \sigma : (w - v) \, dx \right\}.$$

The evolution of smooth processes $q : [0, T] \rightarrow \mathcal{Q}$ is governed by the following *doubly nonlinear subdifferential inclusion* (cf. [CoV90, Col92])

$$\begin{pmatrix} 0 \\ \partial \mathcal{R}(\dot{z}) \end{pmatrix} + \begin{pmatrix} \partial_u \mathcal{E}(t, q) \\ \partial_z \mathcal{E}(t, q) \end{pmatrix} \ni \begin{pmatrix} 0 \\ 0 \end{pmatrix}, \quad (2.4)$$

where $\partial_u \mathcal{E}(t, q) = -\operatorname{div}(\mathbb{C}(\theta):(e(u)-z)) - l(t)$ and $\partial_z \mathcal{E}(t, q) = -\mathbb{C}(\theta):(e(u)-z) + \partial_z h(z, \theta) - \sigma \Delta z$. Using $D_q \mathcal{E}(t, q) \stackrel{\text{def}}{=} (\partial_u \mathcal{E}(t, q), \partial_z \mathcal{E}(t, q))^\top$ and the definition of the subdifferential $\partial \mathcal{R}(\dot{z})$ leads to the *variational inequality*

$$\forall v \in \mathcal{Q} : \langle D_q \mathcal{E}(t, q), v - \dot{q} \rangle_{\mathcal{Q}} + \mathcal{R}(v) - \mathcal{R}(\dot{z}) \geq 0. \quad (2.5)$$

It can be easily seen that (2.5) is equivalent to two local conditions:

$$\begin{aligned} \text{(S)}_{\text{loc}} \quad & \forall v \in \mathcal{Q} : \langle D_q \mathcal{E}(t, q), v \rangle_{\mathcal{Q}} + \mathcal{R}(v) \geq 0, \\ \text{(E)}_{\text{loc}} \quad & \langle D_q \mathcal{E}(t, q), \dot{q} \rangle_{\mathcal{Q}} + \mathcal{R}(\dot{z}) \leq 0. \end{aligned}$$

Since $\mathcal{E}(t, \cdot) : \mathcal{Q} \rightarrow \mathbb{R}$ is convex, our problem has an equivalent *energetic formulation* in the sense of rate-independent processes, for the details the reader is referred to [MiT04, MTL02, MaM05, FrM06, Mie05]. A function $q : [0, T] \rightarrow \mathcal{Q}$ is called an *energetic solution* of the rate-independent problem associated with \mathcal{E} and \mathcal{R} if for all $t \in [0, T]$ the *global stability condition* (S) and the *global energy balance* (E) are satisfied, i.e.

$$\begin{aligned} \text{(S)} \quad & \forall \bar{q} = (\bar{u}, \bar{z}) \in \mathcal{Q} : \mathcal{E}(t, q(t)) \leq \mathcal{E}(t, \bar{q}) + \mathcal{R}(\bar{z} - z(t)), \\ \text{(E)} \quad & \mathcal{E}(t, q(t)) + \int_0^t \mathcal{R}(\dot{z}(s)) \, ds = \mathcal{E}(0, q(0)) + \int_0^t \partial_s \mathcal{E}(s, q(s)) \, ds. \end{aligned}$$

Following the SOUZA ET AL. [SMZ98] and AURICCHIO ET AL. [Aur01, AuP04], we are particularly interested in $h = h_{\text{SA}}$ with

$$h_{\text{SA}}(z, \theta) \stackrel{\text{def}}{=} c_1(\theta) \sqrt{\delta^2 + |z|^2} + c_2(\theta) |z|^2 + \frac{1}{\delta} (|z| - c_3(\theta))_+^3, \quad (2.6)$$

where $c_i(\theta) > 0$, $i = 1, 2, 3$, are given in term of the temperature θ . Observe that $c_1(\theta)$ is an activation threshold for initiation of martensitic phase transformations, $c_2(\theta)$ measures the occurrence of some hardening phenomenon with respect to the internal variable z , and $c_3(\theta)$ represents the maximum modulus of transformation strain that can be obtained by alignment of martensitic variants. Let

$$W_{\text{SA}}(e, z, \theta) \stackrel{\text{def}}{=} \frac{1}{2} (e - z) : \mathbb{C}(\theta) : (e - z) + h_{\text{SA}}(z, \theta).$$

For recent further development we refer to [AuS05, AuS04, AMS07]. The original model is obtained in the limit $\delta \rightarrow 0$ and $\sigma \rightarrow 0$, in this case

$$h_{\text{org}}(z, \theta) \stackrel{\text{def}}{=} c_1(\theta) |z| + c_2(\theta) |z|^2 + \chi(z),$$

where $\chi : \mathbb{R}_{\text{dev}}^{d \times d} \rightarrow [0, +\infty]$ is the indicator function of the ball $\{z \in \mathbb{R}_{\text{dev}}^{d \times d} : |z| \leq c_3(\theta)\}$. For mathematical purposes we need to keep $\delta, \sigma > 0$ fixed.

3 The mathematical assumptions

We clarify now the assumptions and establish some preliminary results that we will use in the next sections. In the Appendix we will show that $h(z, \theta) = h_{\text{SA}}(z, \theta)$ fulfills these assumptions.

Assumptions on h . There exist positive constants $C^h, C_{\theta_j}^h, c_{\theta_j}^h, C_{z\theta}^h, C_z^h$ and $\gamma_d \in [3, \infty)$ with $\gamma_d \leq \frac{2d}{d-2}$ if $d \geq 3$ such that for all $t \in [0, T], \theta \in [\theta_{\min}, \theta_{\max}]$ and $z, \widehat{z} \in \mathbb{R}_{\text{dev}}^{d \times d}$, we have

$$h \in C^3(\mathbb{R}_{\text{dev}}^{d \times d}; C^2([\theta_{\min}, \theta_{\max}])), \quad (3.1a)$$

$$h(z, \theta) \geq C^h(|z|^2 - 1), \quad (3.1b)$$

$$\forall j = 1, 2 : |\partial_\theta^j h(z, \theta)| \leq C_{\theta_j}^h (h(z, \theta) + c_{\theta_j}^h), \quad (3.1c)$$

$$\forall i = 0, 1, 2 \forall j = 0, 1 : \quad (3.1d)$$

$$|\partial_\theta^j \partial_z^i h(z, \theta) - \partial_\theta^j \partial_z^i h(\widehat{z}, \theta)| \leq C_{z\theta}^h (1 + |z| + |\widehat{z}|)^{\gamma_d - i - 1} |z - \widehat{z}|,$$

$$\forall i = 1, 2, 3 \forall j = 0, 1 : |\partial_\theta^j \partial_z^i h(z, \theta)| \leq C_z^h (1 + |z|)^{\gamma_d - i - j}. \quad (3.1e)$$

Assumptions on \mathbb{C} . The elasticity tensor $\mathbb{C}(\theta) : \mathbb{R}_{\text{sym}}^{d \times d} \rightarrow \mathbb{R}_{\text{sym}}^{d \times d}$ is a symmetric positive definite map such that

$$\mathbb{C} \in C^1([\theta_{\min}, \theta_{\max}]; \text{Lin}(\mathbb{R}_{\text{sym}}^{d \times d}, \mathbb{R}_{\text{sym}}^{d \times d})), \quad (3.2a)$$

$$\exists \alpha > 0 \forall e \in \mathbb{R}_{\text{sym}}^{d \times d} \forall \theta \in [\theta_{\min}, \theta_{\max}] : e : \mathbb{C}(\theta) : e \geq \alpha |e|^2. \quad (3.2b)$$

For later use, we define

$$C^{\mathbb{C}} \stackrel{\text{def}}{=} \sup \{ |\mathbb{C}(\theta)| \mid \theta \in [\theta_{\min}, \theta_{\max}] \} \text{ and } C_\theta^{\mathbb{C}} \stackrel{\text{def}}{=} \sup \{ |\partial_\theta \mathbb{C}(\theta)| \mid \theta \in [\theta_{\min}, \theta_{\max}] \}. \quad (3.3)$$

In particular, if $\lambda, \mu \in C^1([\theta_{\min}, \theta_{\max}])$ with $\lambda(\theta) \geq 0$ and $\mu(\theta) \geq \alpha$ then $\mathbb{C}(\theta) : z \stackrel{\text{def}}{=} \lambda(\theta) \text{tr}(z) \mathbf{1} + 2\mu(\theta)z$ satisfies the assumptions given above. Here $\lambda(\theta)$ and $\mu(\theta)$ are temperature dependent Lamé coefficients, and $\mathbf{1}$ denotes the identity matrix. The latter decomposition is not exploited in our analysis but it is clearly suggested by the mechanical application. From (3.1b) and (3.2b) we may deduce that there exist $c, C > 0$ such that

$$\forall e \in \mathbb{R}_{\text{sym}}^{d \times d} \forall z \in \mathbb{R}_{\text{dev}}^{d \times d} : W(e, z, \theta) \geq c(|e|^2 + |z|^2) - C. \quad (3.4)$$

The applied temperature will insert or extract energy according to $\partial_\theta W(e(u), z, \theta_{\text{appl}})$ $\dot{\theta}_{\text{appl}}$. To control this term we assume that θ_{appl} is smooth enough (cf. Section 4) and we prove in the following lemma that the derivatives $\partial_\theta^j W$ exist for $j = 1, 2$ and they can be estimated linearly via W .

Lemma 3.1 *Assume that \mathbb{C} satisfies above assumptions and h satisfies (3.1c). Then there exist $C_0^W, C_1^W > 0$ such that for all $j = 1, 2$,*

$$|\partial_\theta^j W(e, z, \theta)| \leq C_1^W (W(e, z, \theta) + C_0^W). \quad (3.5)$$

Proof. These estimates are obtained using (3.1c) and (3.2). \square

Lemma 3.2 *Under the assumptions of Lemma 3.1, for all $\theta_1 \in [\theta_{\min}, \theta_{\max}]$, we have*

$$W(e, z, \theta_1) + C_0^W \leq \exp(C_1^W |\theta_1 - \theta|)(W(e, z, \theta) + C_0^W). \quad (3.6)$$

Proof. We consider (e, z) to be fixed and define $w(\theta) = W(e, z, \theta) + C_0^W$. Lemma 3.1 provides exactly $|w'(\theta)| \leq C_1^W w(\theta)$, and Gronwall's lemma yields the desired result $w(\theta_1) \leq \exp(C_1^W |\theta_1 - \theta|)w(\theta)$ for all $\theta, \theta_1 \in [\theta_{\min}, \theta_{\max}]$. \square

4 The existence result

For a given temperature profile θ_{appl} and a given external loading l with

$$\theta_{\text{appl}} \in C^1([0, T]; L^\infty(\Omega; [\theta_{\min}, \theta_{\max}])), \quad (4.1a)$$

$$l \in C^1([0, T]; W^{1,2}(\Omega; \mathbb{R}^d)^*), \quad (4.1b)$$

we now study the potential energy \mathcal{E} as defined in (2.2).

Proposition 4.1 *Under the above assumptions the following holds:*

(i) *If for some $(t_*, q) \in [0, T] \times \mathcal{Q}$ we have $\mathcal{E}(t_*, q) < \infty$, then $\mathcal{E}(\cdot, q)$ lies in $C^1([0, T])$ and*

$$\partial_t \mathcal{E}(t, q) = \int_{\Omega} \partial_{\theta} W(e(u), z, \theta_{\text{appl}}(t)) \dot{\theta}_{\text{appl}}(t) \, dx - \langle \dot{l}(t), u \rangle. \quad (4.2)$$

(ii) *There exist $C_0^E, C_1^E > 0$ such that $\mathcal{E}(t, q) < \infty$ implies that $|\partial_t \mathcal{E}(t, q)| \leq C_1^E(\mathcal{E}(t, q) + C_0^E)$.*

(iii) *For each $\varepsilon > 0$ and $E \in \mathbb{R}$ there exists $\delta > 0$ such that $\mathcal{E}(t_1, q) \leq E$ and $|t_1 - t_2| < \delta$ imply $|\partial_t \mathcal{E}(t_1, q) - \partial_t \mathcal{E}(t_2, q)| \leq \varepsilon$.*

Proof. Observe that (3.4) and Korn's inequality (2.1) lead to

$$\mathcal{E}(t, q) \geq \frac{cC_{\text{Korn}}}{2} \|u\|_{W^{1,2}}^2 + \min\left(c, \frac{\sigma}{2}\right) \|z\|_{W^{1,2}}^2 - C|\Omega| - \frac{1}{2cC_{\text{Korn}}} \|l(t)\|_{(W^{1,2})'}^2,$$

which implies that there exist $c_0, C_0 > 0$ such that

$$\mathcal{E}(t, q) \geq c_0 \|q\|_{\mathcal{Q}}^2 - C_0. \quad (4.3)$$

We show now the differentiability of $\mathcal{E}(t, q)$ with respect to t using Lemma 3.1 and assumption (4.1). For all $h \neq 0$ and $t_* + h \in [0, T]$ the mean-value theorem provides some $s \in (0, 1)$ such that

$$\begin{aligned} & \frac{1}{h}(\mathcal{E}(t_*+h, q) - \mathcal{E}(t_*, q)) \\ &= \int_{\Omega} \partial_{\theta} W(e(u), z, \theta_{\text{appl}}) \dot{\theta}_{\text{appl}}(t_*+sh) \, dx - \langle l(t_*+h) - l(t_*), u \rangle. \end{aligned} \quad (4.4)$$

We observe that Lemma 3.2 leads to

$$\sup_{\theta_1 \in [\theta_{\min}, \theta_{\max}]} W(e, z, \theta_1) \leq \exp(c_1^W(\theta_{\max} - \theta_{\min})) (W(e, z, \theta_{\text{appl}}) + C_0^W) - C_0^W. \quad (4.5)$$

Since $\mathcal{E}(t_*, q) < \infty$ we have $0 \leq W(e(u), z, \theta_{\text{appl}}(t)) \in L^1(\Omega)$ which implies that the right-hand side of (4.5) belongs to $L^1(\Omega)$. On the other hand, (4.1a) gives $\dot{\theta}_{\text{appl}} \in C^0([0, T]; L^\infty(\Omega))$ and we may pass to the limit $h \rightarrow 0$ in (4.4) using Lebesgue's theorem. This proves (4.2).

For part (ii), one can see that assumptions (4.1) lead to the following estimate

$$|\partial_t \mathcal{E}(t, q)| \leq \Theta \int_{\Omega} |\partial_{\theta} W(e(u), z, \theta_{\text{appl}})| \, dx + \|\dot{l}(t)\|_{(W^{1,2})'} \|u\|_{W^{1,2}}, \quad (4.6)$$

where $\Theta \stackrel{\text{def}}{=} \|\dot{\theta}_{\text{appl}}\|_{L^\infty}$. Carrying (3.5) for $j = 1$ into (4.6) and using Cauchy-Schwarz's inequality, we have

$$|\partial_t \mathcal{E}(t, q)| \leq \Theta \int_{\Omega} C_1^W (W(e(u), z, \theta_{\text{appl}}) + C_0^W) \, dx + \frac{1}{2} \|\dot{l}(t)\|_{(W^{1,2})'}^2 + \frac{1}{2} \|u\|_{W^{1,2}}^2,$$

which implies that

$$\begin{aligned} |\partial_t \mathcal{E}(t, q)| &\leq C_1^W \Theta \mathcal{E}(t, q) + \frac{1}{2} (1 + C_1^W \Theta) \|u\|_{W^{1,2}}^2 + C_0^W C_1^W |\Omega| \Theta \\ &\quad + \frac{1}{2} \left(C_1^W \|\dot{l}\|_{(W^{1,2})'}^2 + \|\dot{\theta}_{\text{appl}}\|_{W^{1,2}} + \|\dot{l}\|_{(W^{1,2})'}^2 \right). \end{aligned} \quad (4.7)$$

Using (4.3) in (4.7), the desired result (ii) follows immediately.

For part (iii), we use

$$\begin{aligned} |\partial_t \mathcal{E}(t_1, q) - \partial_t \mathcal{E}(t_2, q)| &\leq \Theta \int_{\Omega} |\partial_{\theta} W(e(u), z, \theta_{\text{appl}}(t_1)) - \partial_{\theta} W(e(u), z, \theta_{\text{appl}}(t_2))| \, dx \\ &\quad + \int_{\Omega} |\partial_{\theta} W(e(u), z, \theta_{\text{appl}}(t_1))| \, dx \|\dot{\theta}_{\text{appl}}(t_1) - \dot{\theta}_{\text{appl}}(t_2)\|_{L^\infty} \\ &\quad + \|\dot{l}(t_1) - \dot{l}(t_2)\|_{(W^{1,2})'} \|u\|_{W^{1,2}}. \end{aligned} \quad (4.8)$$

The mean-value theorem provides some $s \in (0, 1)$ such that

$$\begin{aligned} & |\partial_{\theta} W(e(u), z, \theta_{\text{appl}}(t_1)) - \partial_{\theta} W(e(u), z, \theta_{\text{appl}}(t_2))| \\ &= |\partial_{\theta}^2 W(e(u), z, \theta_{\text{appl}}(t_1 + s(t_2 - t_1)))| |\theta_{\text{appl}}(t_1) - \theta_{\text{appl}}(t_2)|. \end{aligned} \quad (4.9)$$

Introducing (3.5) in (4.9) and then using (3.6), we obtain

$$\begin{aligned} & |\partial_\theta W(e(u), z, \theta_{\text{appl}}(t_1)) - \partial_\theta W(e(u), z, \theta_{\text{appl}}(t_2))| \\ & \leq K_1^W (W(e(u), z, \theta_{\text{appl}}(t_1)) + C_0^W) |\theta_{\text{appl}}(t_1) - \theta_{\text{appl}}(t_2)|, \end{aligned} \quad (4.10)$$

where $K_1^W \stackrel{\text{def}}{=} C_1^W \exp(C_1^W |\theta_{\text{max}} - \theta_{\text{min}}|)$. One can see that (3.5) and (3.6) lead to

$$|\partial_\theta W(e(u), z, \theta_{\text{appl}}(t_1))| \leq K_1^W (W(e(u), z, \theta_{\text{appl}}) + C_0^W). \quad (4.11)$$

Carrying (4.10) and (4.11) into (4.8), we obtain

$$\begin{aligned} & |\partial_t \mathcal{E}(t_1, q) - \partial_t \mathcal{E}(t_2, q)| \\ & \leq \int_{\Omega} K_1^W (W(e(u), z, \theta_{\text{appl}}(t_1)) + C_0^W) |\theta_{\text{appl}}(t_1) - \theta_{\text{appl}}(t_2)| \, dx \|\dot{\theta}_{\text{appl}}(t_1)\|_{L^\infty} \\ & \quad + \int_{\Omega} K_1^W (W(e(u), z, \theta_{\text{appl}}(t_1)) + C_0^W) \, dx \|\dot{\theta}_{\text{appl}}(t_1) - \dot{\theta}_{\text{appl}}(t_2)\|_{L^\infty} \\ & \quad + \|\dot{l}(t_1) - \dot{l}(t_2)\|_{(W^{1,2})'} \|u\|_{W^{1,2}}, \end{aligned}$$

which implies that

$$\begin{aligned} & |\partial_t \mathcal{E}(t_1, q) - \partial_t \mathcal{E}(t_2, q)| \\ & \leq \int_{\Omega} K_1^W (\mathcal{E}(t_1, q) + C_0^W) \, dx \|\theta_{\text{appl}}(t_1) - \theta_{\text{appl}}(t_2)\|_{L^\infty} \Theta \\ & \quad + \int_{\Omega} K_1^W (\mathcal{E}(t_1, q) + C_0^W) \, dx \|\dot{\theta}_{\text{appl}}(t_1) - \dot{\theta}_{\text{appl}}(t_2)\|_{L^\infty} \\ & \quad + K_1^W \|\dot{l}(t_1)\|_{(W^{1,2})'} \|u\|_{W^{1,2}} (\|\theta_{\text{appl}}(t_1) - \theta_{\text{appl}}(t_2)\|_{L^\infty} \|\dot{\theta}_{\text{appl}}(t_1)\|_{L^\infty} \\ & \quad + \|\dot{\theta}(t_1) - \dot{\theta}(t_2)\|_{L^\infty}) + \|\dot{l}(t_1) - \dot{l}(t_2)\|_{(W^{1,2})'} \|u\|_{W^{1,2}}. \end{aligned} \quad (4.12)$$

One can observe that (4.1) leads to the following estimate

$$\|\dot{l}(t_1) - \dot{l}(t_2)\|_{(W^{1,2})'} + \|\dot{\theta}_{\text{appl}}(t_1) - \dot{\theta}_{\text{appl}}(t_2)\|_{L^\infty} \leq \omega(|t_1 - t_2|). \quad (4.13)$$

Here $\omega : [0, \infty) \rightarrow [0, \infty)$ is a modulus of continuity, i.e. ω is nondecreasing and $\omega(\tau) \rightarrow 0$ for $\tau \searrow 0$. Since $\mathcal{E}(t_1, q) \leq E$, (4.3) and (4.13) hold, there exists $\bar{c} > 0$ such that

$$|\partial_t \mathcal{E}(t_1, q) - \partial_t \mathcal{E}(t_2, q)| \leq \bar{c} (\omega(|t_1 - t_2|) + |t_1 - t_2|).$$

Thus, the proposition is established. \square

We prove now that the *energetic formulation* (S) and (E) has at least one solution $q : [0, T] \rightarrow \mathcal{Q}$ for a given stable initial datum $q_0 \in \mathcal{Q}$, i.e. q_0 satisfies the *global stability condition* (S) at $t = 0$. The existence theory was developed in [MaM05, Mie05, FrM06] and it is based on incremental minimization problems. More precisely, for a given partition $\Pi = \{0 = t < t_1 < \dots < t_N = T\}$, we define the incremental problem as follows:

$$(\text{IP})_\Pi \left\{ \begin{array}{l} \text{For } k = 1, \dots, N \text{ find} \\ q_k \stackrel{\text{def}}{=} (u_k, z_k) \in \text{Argmin}\{\mathcal{E}(t_k, \tilde{q}) + \mathcal{R}(\tilde{z} - z_k) : \tilde{q} = (\tilde{u}, \tilde{z}) \in \mathcal{Q}\}. \end{array} \right.$$

Define the piecewise constant interpolant $q^\Pi : [0, T] \rightarrow \mathcal{Q}$ with $q^\Pi(t) = q_{j-1}$ for $t \in [t_{j-1}, t_j)$ for $j = 0, \dots, N$. Then, one shows that a subsequence has a limit and this limit function satisfies the *energetic formulation* (S) and (E).

Theorem 4.2 *Assume that \mathcal{E} and \mathcal{R} satisfy the assumptions (2.1), (3.1), (3.2) and (4.1). Let $q_0 \in \mathcal{Q}$ be stable for $t = 0$, i.e. $\mathcal{E}(0, q_0) \leq \mathcal{E}(0, q) + \mathcal{R}(z - z_0)$ for all $q = (u, z) \in \mathcal{Q}$. Then there exists an energetic solution $q = (u, z) : [0, T] \rightarrow \mathcal{Q}$ with $q(0) = q_0$ and*

$$\begin{aligned} u &\in L^\infty([0, T]; W^{1,2}(\Omega; \mathbb{R}^d)), \\ z &\in L^\infty([0, T]; W^{1,2}(\Omega; \mathbb{R}^{d \times d})) \cap BV([0, T]; L^1(\Omega; \mathbb{R}^{d \times d})). \end{aligned}$$

Moreover, let $\Pi_k = \{0 = t_0^k < t_1^k < \dots < t_{N_k}^k = T\}$, $k \in \mathbb{N}$, be a sequence of partitions with fineness $\Delta(\Pi_k) \stackrel{\text{def}}{=} \max\{t_j^k - t_{j-1}^k : j = 1, \dots, N_k\}$ tending to 0 for $k \rightarrow \infty$. Let $q^{\Pi_k} \stackrel{\text{def}}{=} (u^{\Pi_k}, z^{\Pi_k}) : [0, T] \rightarrow \mathcal{Q}$ be the piecewise constant interpolants associated with the incremental problem $(\text{IP})_{\Pi_k}$, then there exist a subsequence $(\bar{u}_n, \bar{z}_n) \stackrel{\text{def}}{=} (u^{\Pi_{k_n}}, z^{\Pi_{k_n}})$ and an energetic solution $\tilde{q} \stackrel{\text{def}}{=} (\tilde{u}, \tilde{z}) : [0, T] \rightarrow \mathcal{Q}$ such that for all $t \in [0, T]$ the following holds

$$\begin{aligned} \bar{z}_n(t) &\rightharpoonup \tilde{z}(t) \text{ in } \mathcal{Z}, \\ \mathcal{E}(t, \bar{q}_n(t)) &\rightarrow \mathcal{E}(t, \tilde{q}(t)), \\ \int_0^t \mathcal{R}(\dot{\bar{z}}_n(s)) \, ds &\rightarrow \int_0^t \mathcal{R}(\dot{\tilde{z}}(s)) \, ds. \end{aligned}$$

Proof. We use the abstract result of [FrM06] which relies on the following abstract assumptions (H1)—(H5), where \mathcal{F} and \mathcal{Z} are considered as topological spaces carrying the weak topology of $W^{1,2}(\Omega)$. All topological notions are to be understood in the “sequential” sense.

$$(H1) \quad \forall z_1, z_2, z_3 \in \mathcal{Z}: \mathcal{R}(z_1) = 0 \Leftrightarrow z_1 = 0 \quad \text{and} \quad \mathcal{R}(z_1 - z_3) \leq \mathcal{R}(z_1 - z_2) + \mathcal{R}(z_2 - z_3),$$

$$(H2) \quad \mathcal{R} : \mathcal{Z} \rightarrow [0, \infty] \text{ is continuous,}$$

$$(H3) \quad \forall t \in [0, T]: \mathcal{E}(t, \cdot) : \mathcal{Q} \rightarrow [0, \infty) \text{ has compact sublevels,}$$

$$(H4) \quad \text{there exist } C_0^E, C_1^E > 0 \text{ such that for all } q \in \mathcal{Q}:$$

$$\mathcal{E}(0, q) < \infty \implies \begin{cases} \partial_t \mathcal{E}(\cdot, q) : [0, T] \rightarrow \mathbb{R} \text{ is continuous and} \\ |\partial_t \mathcal{E}(t, q)| \leq C_1^E (\mathcal{E}(t, q) + C_0^E), \end{cases}$$

$$(H5) \quad \forall E > 0 \forall \varepsilon > 0 \exists \delta > 0 : (\mathcal{E}(t_1, q) \leq E, |t_1 - t_2| \leq \delta) \implies |\partial_t \mathcal{E}(t_1, q) - \partial_t \mathcal{E}(t_2, q)| < \varepsilon.$$

(H1) follows from the definition (2.3) of the dissipation potential \mathcal{R} . Since \mathcal{R} is strongly continuous in $L^1(\Omega)$, the compact embedding of $W^{1,2}(\Omega)$ into $L^1(\Omega)$ provides (H2).

On the one hand, $\mathcal{E}(t, \cdot)$ is coercive because of (3.1b), (3.2b) and (2.1). On the other hand, by $\mathcal{E}(t, \cdot)$ is weakly lower semi-continuous, as the integrand is convex in $(\nabla u, \nabla z)$ and continuous in z . This provides (H3). Finally, (H4) and (H5) were already obtained in Proposition 4.1.

Since the assumptions (H1)—(H5) are fulfilled, the abstract theory is applicable, and the theorem is proved. \square

The above result does not need any convexity assumption on $h(\cdot, \theta)$, hence solutions may have jumps in general and uniqueness can not be expected.

For the original Souza-Auricchio model, i.e. $\delta = 0$ in (2.6), but still $\sigma > 0$, it is also possible to obtain existence of solutions. For the case $\sigma = 0$ the question of existence is still open, even in the isothermal case, see [AMS07].

5 Temporal regularity via uniform convexity

We assume that $h(\cdot, \theta)$ is α_h -uniformly convex on $\mathbb{R}_{\text{dev}}^{d \times d}$, namely there exists a modulus of convexity $\alpha_h > 0$ such that for all $z_0, z_1 \in \mathbb{R}_{\text{dev}}^{d \times d}$ and $\lambda \in [0, 1]$ we have

$$h(z_\lambda, \theta) \leq (1-\lambda)h(z_0, \theta) + \lambda h(z_1, \theta) - \frac{\alpha_h}{2} \lambda(1-\lambda) |z_1 - z_0|^2, \quad (5.1)$$

where $z_\lambda \stackrel{\text{def}}{=} (1-\lambda)z_0 + \lambda z_1$. By (3.2b) the expression $(e-z):\mathbb{C}(\theta):(e-z)$ is α -uniformly convex in $(e-z)$. With $q_\lambda \stackrel{\text{def}}{=} (1-\lambda)q_0 + \lambda q_1$, we conclude

$$\begin{aligned} \exists \widehat{\kappa} > 0 \quad \forall q_0, q_1 \in \mathcal{Q} \quad \forall t \in [0, T] \quad \forall \lambda \in [0, 1] : \\ \mathcal{E}(t, q_\lambda) \leq (1-\lambda)\mathcal{E}(t, q_0) + \lambda\mathcal{E}(t, q_1) - \frac{\widehat{\kappa}}{2} \lambda(1-\lambda) \|q_1 - q_0\|_{\mathcal{B}}^2, \end{aligned} \quad (5.2)$$

where $\widehat{\kappa} \stackrel{\text{def}}{=} \min(\alpha, \alpha_h, \sigma)$ and $\|q\|_{\mathcal{B}}^2 \stackrel{\text{def}}{=} \|e(u) - z\|_{L^2}^2 + \|z\|_{W^{1,2}}^2$. Using Korn's inequality (2.1), we find $\|q\|_{\mathcal{B}} \geq c_0 \|q\|_{\mathcal{Q}}$. Hence, we deduce from (5.2) that

$$\begin{aligned} \forall q_0, q_1 \in \mathcal{Q} \quad \forall t \in [0, T] \quad \forall \lambda \in [0, 1] : \\ \mathcal{E}(t, q_\lambda) \leq (1-\lambda)\mathcal{E}(t, q_0) + \lambda\mathcal{E}(t, q_1) - \frac{\kappa}{2} \lambda(1-\lambda) \|q_1 - q_0\|_{\mathcal{Q}}^2, \end{aligned} \quad (5.3)$$

where $\kappa = \widehat{\kappa} c_0$. In other words, one has proved that $\mathcal{E}(t, q)$ is κ -uniformly convex in the variable q . Observe that (5.3) implies that

$$\forall q, \widehat{q} \in \mathcal{Q} : \mathcal{E}(t, \widehat{q}) \geq \mathcal{E}(t, q) + \langle D_q \mathcal{E}(t, q), \widehat{q} - q \rangle_{\mathcal{Q}} + \frac{\kappa}{2} \|q - \widehat{q}\|_{\mathcal{Q}}^2. \quad (5.4)$$

We establish now an estimate that is crucial to prove the temporal regularity result given in Theorem 5.2.

Lemma 5.1 *Let assumption (3.2) on \mathbb{C} and assumption (4.1) on the loadings be satisfied. Then for all $R > 0$, there exists $C_R > 0$ such that*

$$\begin{aligned} \forall t \in [0, T] \quad \forall q, \hat{q} \in \mathcal{Q} \quad \text{with} \quad \|q\|_{\mathcal{Q}}, \|\hat{q}\|_{\mathcal{Q}} \leq R : \\ |\partial_t \mathcal{E}(t, q) - \partial_t \mathcal{E}(t, \hat{q})| \leq C_R \|q - \hat{q}\|_{\mathcal{Q}}. \end{aligned}$$

Proof. We denote by $w(u, z, \theta) \stackrel{\text{def}}{=} \frac{1}{2}(e(u) - z) : \partial_{\theta} \mathbb{C}(\theta) : (e(u) - z)$. First, we point out that

$$\partial_t \mathcal{E}(t, q) = \int_{\Omega} \partial_{\theta} W(e(u), z, \theta_{\text{appl}}) \dot{\theta}_{\text{appl}} \, dx - \langle \dot{l}(t), u \rangle, \quad (5.5)$$

where $\partial_{\theta} W(e(u), z, \theta) = w(u, z, \theta) + \partial_{\theta} h(z, \theta)$. Then, we deduce from (5.5) and (4.1b) that

$$|\partial_t \mathcal{E}(t, q) - \partial_t \mathcal{E}(t, \hat{q})| \leq I \|\dot{\theta}_{\text{appl}}\|_{L^{\infty}} + \|\dot{l}(t)\|_{(W^{1,2})'} \|u - \hat{u}\|_{W^{1,2}}, \quad (5.6)$$

where $I \stackrel{\text{def}}{=} \int_{\Omega} |\partial_{\theta} W(e(u), z, \theta_{\text{appl}}) - \partial_{\theta} W(e(\hat{u}), \hat{z}, \theta_{\text{appl}})| \, dx$. This gives

$$I \leq \int_{\Omega} |w(u, z, \theta_{\text{appl}}) - w(\hat{u}, \hat{z}, \theta_{\text{appl}})| \, dx + \int_{\Omega} |\partial_{\theta} h(z, \theta_{\text{appl}}) - \partial_{\theta} h(\hat{z}, \theta_{\text{appl}})| \, dx.$$

The first integral is estimated by using (3.3) and Cauchy-Schwarz's inequality. The second one by (3.1d) with $i = 0$ and $j = 1$ and Hölder's inequality to give

$$I \leq C_{\theta}^{\mathbb{C}} (\|q\|_{\mathcal{Q}} + \|\hat{q}\|_{\mathcal{Q}}) \|q - \hat{q}\|_{\mathcal{Q}} + C_{z\theta}^h \|1 + |z| + |\hat{z}|\|_{L^{\gamma_d}}^{\gamma_d - 1} \|z - \hat{z}\|_{L^{\gamma_d}}. \quad (5.7)$$

Since $W^{1,2}(\Omega) \subset L^{\gamma_d}(\Omega)$ (recall that $\gamma_d \leq \frac{2d}{d-2}$ if $d \geq 3$), then the last term on the right-hand side of (5.7) is estimated by $CC_{z\theta}^h (1 + \|z\|_{W^{1,2}} + \|\hat{z}\|_{W^{1,2}})^{\gamma_d - 1} \|z - \hat{z}\|_{W^{1,2}}$ where $C > 0$. Then, we deduce that

$$I \leq \max(C_{\theta}^{\mathbb{C}}, CC_{z\theta}^h) (1 + \|q\|_{\mathcal{Q}} + \|\hat{q}\|_{\mathcal{Q}})^{\gamma_d - 1} \|q - \hat{q}\|_{\mathcal{Q}}. \quad (5.8)$$

Introducing (5.8) in (5.6) the assertion (5.5) follows. \square

Theorem 5.2 (Lipschitz continuity). *Assume that (3.1a), (3.1c) for $j=1$, (3.3), (4.1), and (5.4) hold. Then any energetic solution q is Lipschitz continuous. In fact, let $R \stackrel{\text{def}}{=} \|q\|_{L^{\infty}([0, T]; \mathcal{Q})}$ and $C_R > 0$ given by Lemma 5.1, then $\|\dot{q}(t)\|_{\mathcal{Q}} \leq \frac{C_R}{\kappa}$ for a.e. $t \in [0, T]$ where κ is defined in (5.3).*

Proof. Considering (5.4) for $t \stackrel{\text{def}}{=} s$ and $q \stackrel{\text{def}}{=} q(s)$ we have

$$\forall \hat{q} \in \mathcal{Q} : \mathcal{E}(s, \hat{q}) \geq \mathcal{E}(s, q(s)) + \langle D_q \mathcal{E}(s, q(s)), \hat{q} - q(s) \rangle_{\mathcal{Q}} + \frac{\kappa}{2} \|\hat{q} - q(s)\|_{\mathcal{Q}}^2. \quad (5.9)$$

For arbitrary $s \in [0, T]$ we know that $q(s)$ fulfills $(S)_{\text{loc}}$. Choosing $v \stackrel{\text{def}}{=} \hat{q} - q(s)$ in $(S)_{\text{loc}}$ we deduce from (5.9) that for all $\hat{q} \in \mathcal{Q}$ we have

$$\frac{\kappa}{2} \|\hat{q} - q(s)\|_{\mathcal{Q}}^2 \leq \mathcal{E}(s, \hat{q}) - \mathcal{E}(s, q(s)) + \mathcal{R}(\hat{z} - z(s)). \quad (5.10)$$

Then, for all $t \in [0, T]$ and $s \in [0, t]$, we have

$$\begin{aligned}
\frac{\kappa}{2} \|q(t) - q(s)\|_{\mathcal{Q}}^2 &\leq \mathcal{E}(s, q(t)) - \mathcal{E}(s, q(s)) + \mathcal{R}(z(t) - z(s)) \\
&\leq \mathcal{E}(s, q(t)) - \mathcal{E}(s, q(s)) + \int_s^t \mathcal{R}(\dot{z}(r)) \, dr \\
&= - \int_s^t \partial_r \mathcal{E}(r, q(t)) \, dr + \int_s^t \partial_r \mathcal{E}(r, q(r)) \, dr \\
&\leq C_R \int_s^t \|q(r) - q(t)\|_{\mathcal{Q}} \, dr.
\end{aligned}$$

The first inequality is obtained by choosing $\hat{q} \stackrel{\text{def}}{=} q(t)$ in (5.9), the second one comes from the convexity of $\mathcal{R}(\cdot)$, the third identity follows from the energy identity (E), and the last one results from (5.5). Note that this estimate is exactly the assumptions of the following Lemma 5.3, hence the result follows. \square

Lemma 5.3 *Let $q \in L^\infty([0, T]; \mathcal{Q})$ and $C > 0$ be given such that for all $t \in [0, T]$ and $s \in [0, t]$ we have*

$$\frac{\kappa}{2} \|q(t) - q(s)\|_{\mathcal{Q}}^2 \leq C \int_s^t \|q(r) - q(t)\|_{\mathcal{Q}} \, dr.$$

Then, $q \in C^{\text{Lip}}([0, T]; \mathcal{Q})$ with $\|\dot{q}(t)\|_{\mathcal{Q}} \leq \frac{C}{\kappa}$ for a.e. $t \in [0, T]$.

Proof. The proof is obtained using the same techniques detailed in the proof of Theorem 7.5 in [MiT04]. Since it is quite a routine to adapt this proof to our case, we let the verification to the reader. \square

6 Uniqueness result

Uniqueness results in rate-independent hysteresis models are rather exceptional, as usually one needs strong assumptions on the nonlinearities, see [MiT04, MiR07]. To show uniqueness we consider two solutions q_0 and q_1 and prove our result using the techniques developed in [MiT04]. For this we introduce now some convenient notations. For $i = 0, 1$ and $j = 0, 1, 2$, let

$$w_i \stackrel{\text{def}}{=} e(u_i) - z_i \quad \text{and} \quad D_q^j \mathcal{E}_i \stackrel{\text{def}}{=} D_q^j \mathcal{E}(t, q_i(t)).$$

We denote by $\mathcal{Q}_R \stackrel{\text{def}}{=} \{q \in \mathcal{Q} : \|q\|_{\mathcal{Q}} \leq R\}$.

Proposition 6.1 *Assume that (3.1d), (3.1e), (3.2a) and (4.1) hold. Then*

$$D_q \mathcal{E}(t, q)[\widehat{q}] = \int_{\Omega} (\widehat{w} : \mathbb{C}(\theta_{\text{appl}}) : w + \partial_z h(z, \theta_{\text{appl}}) : \widehat{z} + \sigma \nabla z : \nabla \widehat{z}) \, dx - \langle l(t), \widehat{u} \rangle, \quad (6.1a)$$

$$\partial_t D_q \mathcal{E}(t, q)[\widehat{q}] = \int_{\Omega} \dot{\theta}_{\text{appl}} (\widehat{w} : \partial_{\theta} \mathbb{C}(\theta_{\text{appl}}) : w + \partial_{\theta} \partial_z h(z, \theta_{\text{appl}}) : \widehat{z}) \, dx - \langle \dot{l}(t), \widehat{u} \rangle, \quad (6.1b)$$

$$D_q^2 \mathcal{E}(t, q)[\widehat{q}, \widehat{q}] = \int_{\Omega} (\widehat{w} : \mathbb{C}(\theta_{\text{appl}}) : \widehat{w} + \widehat{z} : \partial_z^2 h(z, \theta_{\text{appl}}) : \widehat{z} + \sigma |\nabla \widehat{z}|^2) \, dx, \quad (6.1c)$$

where $w \stackrel{\text{def}}{=} e(u) - z$ and $\widehat{w} \stackrel{\text{def}}{=} e(\widehat{u}) - \widehat{z}$. For $R > 0$, we have $\mathcal{E}(t, \cdot) \in C^{2, \text{Lip}}(\mathcal{Q}_R; \mathbb{R})$.

Proof. First, using (3.1e) and (3.2a), one can deduce from Lebesgue's theorem that $D_q \mathcal{E}(t, q)$, $\partial_t D_q \mathcal{E}(t, q)$ and $D_q^2 \mathcal{E}(t, q)$ exist and (6.1) holds. On the other hand, one observes using (3.3) and (3.1d) with $i = 2$ and $j = 0$ that

$$|D_q^2 \mathcal{E}(t, q)[\widehat{q}, \widehat{q}]| \leq C_{\theta}^{\mathbb{C}} \|\widehat{w}\|_{L^2}^2 + C_z^h \|1 + |z|\|_{L^{\gamma_d}}^{\gamma_d - 2} \|\widehat{z}\|_{L^{\gamma_d}}^2 + \sigma \|\nabla \widehat{z}\|_{L^2}^2. \quad (6.2)$$

Since $W^{1,2}(\Omega) \subset L^{\gamma_d}(\Omega)$ with $\gamma_d \leq \frac{2d}{d-2}$, the second term on the right side of (6.2) is estimated by $C_1 C_z^h (1 + \|z\|_{W^{1,2}})^{\gamma_d - 2} \|\widehat{z}\|_{W^{1,2}}^2$ where $C_1 > 0$ and it follows that

$$|D_q^2 \mathcal{E}(t, q)[\widehat{q}, \widehat{q}]| \leq C(1 + \|q\|_{\mathcal{Q}})^{\gamma_d - 2} \|\widehat{q}\|_{\mathcal{Q}}^2, \quad (6.3)$$

where $C \stackrel{\text{def}}{=} \max(2C_{\theta}^{\mathbb{C}}, C_1 C_z^h, \sigma)$. Observe now that (3.1d) with $i = 2$ and $j = 0$ and Hölder's inequality give

$$|D_q^2 \mathcal{E}_1[\widehat{q}, \widehat{q}] - D_q^2 \mathcal{E}_0[\widehat{q}, \widehat{q}]| \leq C_{z\theta}^h \|1 + |z_0| + |z_1|\|_{L^{\gamma_d}}^{\gamma_d - 3} \|\widehat{z}\|_{L^{\gamma_d}}^2 \|z_1 - z_0\|_{L^{\gamma_d}}.$$

Since $W^{1,2}(\Omega) \subset L^{\gamma_d}(\Omega)$ with $\gamma_d \leq \frac{2d}{d-2}$ then the latter estimate implies that there exists $C_2 > 0$ such that

$$|D_q^2 \mathcal{E}_1[\widehat{q}, \widehat{q}] - D_q^2 \mathcal{E}_0[\widehat{q}, \widehat{q}]| \leq C_2 C_{z\theta}^h (1 + \|q_0\|_{\mathcal{Q}} + \|q_1\|_{\mathcal{Q}})^{\gamma_d - 3} \|\widehat{q}\|_{\mathcal{Q}}^2 \|q_1 - q_0\|_{\mathcal{Q}}. \quad (6.4)$$

Hence, $\mathcal{E}(t, \cdot) \in C^{2, \text{Lip}}(\mathcal{Q}_R; \mathbb{R})$ for every $R > 0$. \square

We establish now some estimates in the following lemma that are crucial to obtain the uniqueness result given in Theorem 6.3.

Lemma 6.2 *Assume that (3.1d), (3.1e), (3.2a) and (4.1) hold. Then for each $R > 0$, there exist $C_1, C_2 > 0$ such that for all $q_0, q_1 \in \mathcal{Q}_R$, we have*

$$\|\partial_t D_q \mathcal{E}_1 - \partial_t D_q \mathcal{E}_0\|_{\mathcal{Q}'} \leq C_1 \|q_1 - q_0\|_{\mathcal{Q}}, \quad (6.5a)$$

$$\|D_q \mathcal{E}_{1-i} - D_q \mathcal{E}_i + D_q^2 \mathcal{E}_i [q_i - q_{1-i}]\|_{\mathcal{Q}'} \leq C_2 \|q_1 - q_0\|_{\mathcal{Q}}^2. \quad (6.5b)$$

Proof. Defining $W_i \stackrel{\text{def}}{=} W(e(u_i), z_i, \theta_{\text{appl}})$ for $i = 0, 1$, we observe that

$$\|\partial_t D_q \mathcal{E}_1 - \partial_t D_q \mathcal{E}_0\|_{\mathcal{Q}'} = \sup_{\|\widehat{q}\|_{\mathcal{Q}} \leq 1} \left| \int_{\Omega} \dot{\theta}_{\text{appl}} (\partial_{\theta} D_q W_1 - \partial_{\theta} D_q W_0) : \widehat{q} \, dx \right|,$$

where $\widehat{q} = (\widehat{u}, \widehat{z})^\top \in \mathcal{Q}$. With $\widehat{w} = e(\widehat{u}) - \widehat{z}$ and $w_j = e(u_j) + z_j$ it follows

$$\begin{aligned} \|\partial_t D_q \mathcal{E}_1 - \partial_t D_q \mathcal{E}_0\|_{\mathcal{Q}'} &\leq \sup_{\|(\widehat{u}, \widehat{z})\|_{W^{1,2}} \leq 1} \left(\int_{\Omega} |\partial_\theta \partial_z h(z_1, \theta_{\text{appl}}) - \partial_\theta \partial_z h(z_0, \theta_{\text{appl}})| |\widehat{z}| \, dx \right. \\ &\quad \left. + \int_{\Omega} |(w_1 - w_0) : \partial_\theta \mathbb{C}(\theta_{\text{appl}}) : \widehat{w}| \, dx \right) \Theta, \end{aligned} \quad (6.6)$$

where $\Theta \stackrel{\text{def}}{=} \|\dot{\theta}_{\text{appl}}\|_{L^\infty} < \infty$ due to (4.1a). On the one hand, using (3.1d), with $i = 1$ and $j = 1$, and Cauchy-Schwarz's inequality one has

$$\int_{\Omega} |\partial_\theta \partial_z h(z_1, \theta_{\text{appl}}) - \partial_\theta \partial_z h(z_0, \theta_{\text{appl}})| |\widehat{z}| \, dx \leq C_{z\theta}^h (1 + |z_0| + |z_1| \|L^{\gamma_d}\|^{-1} \|z_1 - z_0\|_{L^{\gamma_d}}) \|\widehat{z}\|_{L^{\gamma_d}}.$$

Since $W^{1,2}(\Omega) \subset L^{\gamma_d}(\Omega)$ with $\gamma_d \leq \frac{2d}{d-2}$, we deduce from the latter inequality that there exists $C > 0$ such that

$$\begin{aligned} &\int_{\Omega} |\partial_\theta \partial_z h(z_1, \theta_{\text{appl}}) - \partial_\theta \partial_z h(z_0, \theta_{\text{appl}})| |\widehat{z}| \, dx \\ &\leq CC_{z\theta}^h (1 + \|z_0\|_{W^{1,2}} + \|z_1\|_{W^{1,2}})^{\gamma_d - 2} \|z_1 - z_0\|_{W^{1,2}} \|\widehat{z}\|_{W^{1,2}}. \end{aligned} \quad (6.7)$$

On the other hand, using (3.3) and Cauchy-Schwarz's inequality, we obtain

$$\int_{\Omega} |\partial_\theta \mathbb{C}(\theta_{\text{appl}})| |w_1 - w_0| |\widehat{w}| \, dx \leq C_{z\theta}^{\mathbb{C}} (\|u_1 - u_0\|_{W^{1,2}} + \|z_1 - z_0\|_{L^2}) \|\widehat{q}\|_{W^{1,2}}. \quad (6.8)$$

Introducing (6.7) and (6.8) in (6.6), we obtain (6.5a).

For $i = 0, 1$, let us evaluate now

$$\begin{aligned} &\|D_q \mathcal{E}_{1-i} - D_q \mathcal{E}_i + D_q^2 \mathcal{E}_i [q_i - q_{1-i}]\|_{\mathcal{Q}'} \\ &= \left\| \int_0^1 (D_q \mathcal{E}(t, q_i + \rho(q_{1-i} - q_i)) + D_q^2 \mathcal{E}_i) [q_i - q_{1-i}] \, d\rho \right\|_{\mathcal{Q}'}, \end{aligned}$$

which implies by using (6.4) that there exists $C_R > 0$ such that

$$\|D_q \mathcal{E}_{1-i} - D_q \mathcal{E}_i + D_q^2 \mathcal{E}_i [q_i - q_{1-i}]\|_{\mathcal{Q}'} \leq \int_0^1 C_R \rho \|q_{1-i} - q_i\|_{\mathcal{Q}}^2 \, d\rho = \frac{C_R}{2} \|q_0 - q_1\|_{\mathcal{Q}}^2. \quad (6.9)$$

Thus, (6.5b) follows. \square

Theorem 6.3 *Assume that (3.1d), (3.1e), (3.2a) and (4.1) hold. Then for each stable initial condition q_0 , there exists a unique energetic solution q . In particular, for each $R > 0$ there exist constants $C, c > 0$ such that for all stable initial conditions $q_0(0), q_1(0) \in \mathcal{Q}_R$, the solutions q_0 and q_1 satisfy*

$$\|q_1(t) - q_0(t)\|_{\mathcal{Q}} \leq C \exp(ct) \|q_1(0) - q_0(0)\|_{\mathcal{Q}} \text{ for all } t \in [0, T].$$

Proof. The uniqueness result will follow from the estimates obtained in the Lemma 6.2 and Gronwall's lemma. Given two solutions q_0 and q_1 , there exists $R > 0$ such that $\|q_j\|_{C^0([0,T],\mathcal{Q})} \leq R$ for $j = 0, 1$. Define

$$\gamma(t) \stackrel{\text{def}}{=} \langle D_q \mathcal{E}_1 - D_q \mathcal{E}_0, q_1 - q_0 \rangle.$$

Then, by κ -uniform convexity (see (5.4)), we have

$$\|q_1(t) - q_0(t)\|_{\mathcal{Q}}^2 \leq \frac{\gamma(t)}{\kappa}. \quad (6.10)$$

On the other hand, the derivative of $\gamma(t)$ denoted by $\dot{\gamma}(t)$ is given by

$$\begin{aligned} \dot{\gamma}(t) &= 2\langle D_q \mathcal{E}_1 - D_q \mathcal{E}_0, \dot{q}_1 - \dot{q}_0 \rangle + \langle \partial_t D_q \mathcal{E}_1 - \partial_t D_q \mathcal{E}_0, q_1 - q_0 \rangle \\ &\quad + \sum_{i=0}^1 \langle D_q \mathcal{E}_{1-i} - D_q \mathcal{E}_i + D_q^2 \mathcal{E}_i [q_i - q_{i-1}], \dot{q}_i \rangle. \end{aligned} \quad (6.11)$$

Taking the test functions $v \stackrel{\text{def}}{=} \dot{q}_{1-i}$ in (2.5) for $i = 0, 1$ and then adding the both inequalities, we obtain

$$\langle D_q \mathcal{E}_1 - D_q \mathcal{E}_0, \dot{q}_1 - \dot{q}_0 \rangle \leq 0. \quad (6.12)$$

Using (6.12) in (6.11), we have

$$\begin{aligned} \dot{\gamma}(t) &\leq \langle \partial_t D_q \mathcal{E}_1 - \partial_t D_q \mathcal{E}_0, q_1 - q_0 \rangle + \sum_{i=0}^1 \langle D_q \mathcal{E}_{1-i} - D_q \mathcal{E}_i + D_q^2 \mathcal{E}_i [q_i - q_{i-1}], \dot{q}_i \rangle \\ &\leq \|\partial_t D_q \mathcal{E}_1 - \partial_t D_q \mathcal{E}_0\|_{\mathcal{Q}'} \|q_1 - q_0\|_{\mathcal{Q}} + \sum_{i=0}^1 \|D_q \mathcal{E}_{1-i} - D_q \mathcal{E}_i + D_q^2 \mathcal{E}_i [q_i - q_{i-1}]\|_{\mathcal{Q}'} \|\dot{q}_i\|_{\mathcal{Q}}. \end{aligned}$$

Then, Theorem 5.2 and Lemma 6.2 enable us to deduce

$$\dot{\gamma}(t) \leq C_3 \|q_1(t) - q_0(t)\|_{\mathcal{Q}}^2 \leq \frac{C_3}{\kappa} \gamma(t) \quad \text{with } C_3 = 2(C_1 + C_2 C_R).$$

Hence, the classical Gronwall's lemma and (6.10) lead to

$$\|q_1(t) - q_0(t)\|_{\mathcal{Q}}^2 \leq \frac{1}{\kappa} \exp\left(\frac{C_3}{\kappa} t\right) \gamma(0). \quad (6.13)$$

Using $q_0(0), q_1(0) \in \mathcal{Q}_R$ and $\mathcal{E}(0, \cdot) \in C^{1,\text{Lip}}(\mathcal{Q}_R; \mathbb{R})$ we have

$$\gamma(0) \leq C \|q_0(0) - q_1(0)\|_{\mathcal{Q}}^2,$$

with $C > 0$, and the result follows. \square

A Appendix: On the Souza-Auricchio model

We prove now that the assumptions on h introduced in Section 3 are satisfied for h_{SA} given in (2.6). More precisely, we establish the following lemma:

Lemma A.1 *Assume that $c_i \in C^2([\theta_{\min}, \theta_{\max}])$, $i = 1, 2, 3$, for all $\theta \in [\theta_{\min}, \theta_{\max}]$ and $c_i(\theta) > 0$. Then there exist positive constants $C^h, C_{\theta_j}^h, c_{\theta_j}^h, C_\theta^h, C_{z\theta}^h, C_z^h$ such that for all $t \in [0, T]$, $\theta \in [\theta_{\min}, \theta_{\max}]$, $z, \widehat{z} \in \mathbb{R}_{\text{dev}}^{d \times d}$, we have,*

$$h_{SA}(\cdot, \theta) \text{ is } \alpha_{h_{SA}}\text{-uniformly convex and belongs to } C^3(\mathbb{R}_{\text{dev}}^{d \times d}) \text{ with} \quad (\text{A.1a})$$

$$\alpha_{h_{SA}} \stackrel{\text{def}}{=} \min\{c_1(\theta) : \theta \in [\theta_{\min}, \theta_{\max}]\},$$

$$h_{SA}(z, \theta) \geq C^h(|z|^2 - 1), \quad (\text{A.1b})$$

$$\forall j = 1, 2 : |\partial_\theta^j h_{SA}(z, \theta)| \leq C_{\theta_j}^h(h_{SA}(z, \theta) + c_{\theta_j}^h), \quad (\text{A.1c})$$

$$\forall i = 0, 1 : |\partial_\theta \partial_z^i h_{SA}(z, \theta) - \partial_\theta \partial_z^i h_{SA}(\widehat{z}, \theta)| \leq C_{z\theta}^h(1 + |z| + |\widehat{z}|)|z - \widehat{z}|, \quad (\text{A.1d})$$

$$\forall i = 0, 1, 2 : |\partial_z^i h_{SA}(z, \theta) - \partial_z^i h_{SA}(\widehat{z}, \theta)| \leq C_z^h(1 + |z| + |\widehat{z}|)^{3-i}|z - \widehat{z}|, \quad (\text{A.1e})$$

$$\forall i = 1, 2, 3 \forall j = 0, 1 : |\partial_\theta^j \partial_z^i h_{SA}(z, \theta)| \leq C_z^h(1 + |z|)^{3-i-j}. \quad (\text{A.1f})$$

Proof. Note that $h_{SA}(\cdot, \theta)$ is a sum of three non-negative convex and belonging to $C^3(\mathbb{R}_{\text{dev}}^{d \times d})$:

$$h_1(z, \theta) \stackrel{\text{def}}{=} c_1(\theta)\sqrt{\delta^2 + |z|^2}, \quad h_2(z, \theta) \stackrel{\text{def}}{=} c_2(\theta)|z|^2, \quad h_3(z, \theta) \stackrel{\text{def}}{=} \frac{1}{\delta}(|z| - c_3(\theta))_+^3.$$

Moreover, the quadratic term is α -uniformly convex and coercive. Hence (A.1a) and (A.1b) hold. Define for $i = 1, 2, 3$, $c'_i(\theta) \stackrel{\text{def}}{=} \partial_\theta c_i(\theta)$ and $c''_i(\theta) \stackrel{\text{def}}{=} \partial_\theta^2 c_i(\theta)$. The estimates (A.1c) will result from the application of Young's inequality. First, we differentiate $h_{SA}(z, \theta)$ with respect to θ and we obtain easily the following inequality

$$|\partial_\theta h_{SA}(z, \theta)| \leq |c'_1(\theta)|\sqrt{\delta^2 + |z|^2} + |c'_2(\theta)||z|^2 + \frac{3}{\delta}|c'_3(\theta)|(|z|^2 - c_3(\theta))_+^2. \quad (\text{A.2})$$

The last term on the right-hand side of (A.2) is estimated by Young's inequality and then (A.1c) for $j = 1$ follows.

We differentiate $\partial_\theta h_{SA}(z, \theta)$ with respect to θ and obtain the estimate

$$\begin{aligned} |\partial_\theta^2 h_{SA}(z, \theta)| &\leq |c''_1(\theta)|\sqrt{\delta^2 + |z|^2} + |c''_2(\theta)||z|^2 + \frac{3}{\delta}|2c'_3(\theta)|(|z|^2 - c_3(\theta))_+ \\ &\quad + \frac{3}{\delta}|c''_3(\theta)|(|z|^2 - c_3(\theta))_+^2. \end{aligned} \quad (\text{A.3})$$

Once again, we use Young's inequality to estimate the last two terms on the right-hand side of (A.3) and obtain (A.1c) for $j = 2$.

We note that (A.1d) will be obtained by a simple calculus explained below and since it is quite a routine, we let the details to the reader. First, we define $\mu_i \stackrel{\text{def}}{=}$

$\sup_{\theta \in [\theta_{\min}, \theta_{\max}]} |c_i(\theta)|$ and $\eta_i \stackrel{\text{def}}{=} \sup_{\theta \in [\theta_{\min}, \theta_{\max}]} |c'_i(\theta)|$, $i = 1, 2, 3$. On the one hand, using the previous notation, we obtain

$$\begin{aligned} |\partial_\theta h_{\text{SA}}(z, \theta) - \partial_\theta h_{\text{SA}}(\widehat{z}, \theta)| &\leq \eta_1 \left| \sqrt{\delta^2 + |z|^2} - \sqrt{\delta^2 + |\widehat{z}|^2} \right| + \eta_2 \left| |z|^2 - |\widehat{z}|^2 \right| \\ &\quad + \frac{3\eta_3}{\delta} \left| (|z| - c_3(\theta))_+^2 - (|\widehat{z}| - c_3(\theta))_+^2 \right|, \end{aligned}$$

which implies that

$$|\partial_\theta h_{\text{SA}}(z, \theta) - \partial_\theta h_{\text{SA}}(\widehat{z}, \theta)| \leq |z - \widehat{z}| \left[\left(\frac{\eta_1}{\delta^2} + \eta_2 \right) (|z| + |\widehat{z}|) + (2\eta_3 + |z| + |\widehat{z}|) \right]. \quad (\text{A.4})$$

Then, the desired inequality (A.1d) for $i = 0$ follows from (A.4). On the other hand, one can observe that

$$\begin{aligned} |\partial_\theta \partial_z h_{\text{SA}}(z, \theta) - \partial_\theta \partial_z h_{\text{SA}}(\widehat{z}, \theta)| &\leq \eta_1 \left| \frac{z}{\sqrt{\delta^2 + |z|^2}} - \frac{\widehat{z}}{\sqrt{\delta^2 + |\widehat{z}|^2}} \right| + 2\eta_2 |z - \widehat{z}| \\ &\quad + \frac{12\eta_3}{\delta} \left| z(|z| - c_3(\theta))_+ - \widehat{z}(|\widehat{z}| - c_3(\theta))_+ \right|, \end{aligned}$$

which leads to

$$\begin{aligned} &|\partial_\theta \partial_z h_{\text{SA}}(z, \theta) - \partial_\theta \partial_z h_{\text{SA}}(\widehat{z}, \theta)| \\ &\leq |z - \widehat{z}| \left[\frac{\eta_1}{\delta} \left(1 + \frac{1}{\delta} \right) (1 + |z| + |\widehat{z}|) + 2\eta_2 + \frac{12\eta_3}{\delta} (1 + |z| + |\widehat{z}|) \right]. \end{aligned}$$

Then, one easily deduces (A.1d) for $i = 1$ by using the latter inequality.

One can show easily that

$$|h_{\text{SA}}(z, \theta) - h_{\text{SA}}(\widehat{z}, \theta)| \leq \left(\mu_1 + \frac{\mu_2}{2\delta} \right) (|z| + |\widehat{z}|) |z - \widehat{z}| + (|z| + |\widehat{z}|)^2 |z - \widehat{z}|,$$

which gives (A.1e) for $i = 0$. We may also observe that

$$|\partial_z h_{\text{SA}}(z, \theta) - \partial_z h_{\text{SA}}(\widehat{z}, \theta)| \leq c_\delta \mu_1 (1 + |z| + |\widehat{z}|) |z - \widehat{z}| + \mu_2 |z - \widehat{z}| + \frac{6}{\delta} (1 + |z| + |\widehat{z}|) |z - \widehat{z}|,$$

where $c_\delta \stackrel{\text{def}}{=} \max\left(\frac{1}{\delta}, \frac{1}{\delta^2}\right)$. Then (A.1e) for $i = 1$ follows from the latter estimate. Let us remark now that there exists $C > 0$ such that

$$|\partial_z^2 h_{\text{SA}}(z, \theta) - \partial_z^2 h_{\text{SA}}(\widehat{z}, \theta)| \leq C c_\delta (\mu_1 (|z| + |\widehat{z}|) |z - \widehat{z}| + (1 + |z| + |\widehat{z}|) |z - \widehat{z}|),$$

which implies (A.1e) for $i = 2$.

Finally, one can easily obtain (A.1f), the verification is let to the reader. \square

Acknowledgements. A.P. was supported by the Deutsche Forschungsgemeinschaft within the project C18 “Analysis and numerics of multidimensional models for elastic phase transformation in a shape-memory alloys” of the DFG Research Center MATHEON.

References

- [AMS07] F. AURICCHIO, A. MIELKE, and U. STEFANELLI. A rate-independent model for the isothermal quasi-static evolution of shape-memory materials. *M³AS Math. Models Meth. Appl. Sci.*, 2007. To appear. WIAS Preprint 1170.
- [AuP02] F. AURICCHIO and L. PETRINI. Improvements and algorithmical considerations on a recent three-dimensional model describing stress-induced solid phase transformations. *Int. J. Numer. Meth. Engng.*, 55, 1255–1284, 2002.
- [AuP04] F. AURICCHIO and L. PETRINI. A three-dimensional model describing stress-temperature induced solid phase transformations. Part II: thermomechanical coupling and hybrid composite applications. *Int. J. Numer. Meth. Engng.*, 61, 716–737, 2004.
- [Aur01] F. AURICCHIO. A robust integration algorithm for a finite-strain shape-memory-alloy superelastic model. *Int. J. Plasticity*, 17, 971–990, 2001.
- [AuS04] F. AURICCHIO and U. STEFANELLI. Numerical treatment of a 3D super-elastic constitutive model. *Int. J. Numer. Meth. Engng.*, 61, 142–155, 2004.
- [AuS05] F. AURICCHIO and U. STEFANELLI. Well-posedness and approximation for a one-dimensional model for shape memory alloys. *M3AS: Math. Models Meth. Appl. Sci.*, 15, 1301–1327, 2005.
- [BC*04] S. BARTELS, C. CARSTENSEN, K. HACKL, and U. HOPPE. Effective relaxation for microstructure simulations: algorithms and applications. *Comput. Methods Appl. Mech. Engng.*, 193, 5143–5175, 2004.
- [CHM02] C. CARSTENSEN, K. HACKL, and A. MIELKE. Non-convex potentials and microstructures in finite-strain plasticity. *Proc. Royal Soc. London, Ser. A*, 458, 299–317, 2002.
- [Col92] P. COLLI. On some doubly nonlinear evolution equations in Banach spaces. *Japan J. Indust. Appl. Math.*, 9, 181–203, 1992.
- [CoV90] P. COLLI and A. VISINTIN. On a class of doubly nonlinear evolution equations. *Comm. Partial Differential Equations*, 15(5), 737–756, 1990.
- [DuL76] G. DUVAUT and J.-L. LIONS. *Inequalities in mechanics and physics*. Springer-Verlag, Berlin, 1976. Translated from the French by C. W. John, Grundlehren der Mathematischen Wissenschaften, 219.
- [FrM06] G. FRANCFORT and A. MIELKE. Existence results for a class of rate-independent material models with nonconvex elastic energies. *J. reine angew. Math.*, 595, 55–91, 2006.
- [GMH02] S. GOVINDJEE, A. MIELKE, and G. HALL. The free-energy of mixing for n -variant martensitic phase transformations using quasi-convex analysis. *J. Mech. Physics Solids*, 50, 1897–1922, 2002. Erratum and Correct Reprinting: 51(4) 2003, pp. 763 & I-XXVI.

- [KMR05] M. KRUŽÍK, A. MIELKE, and T. ROUBÍČEK. Modelling of microstructure and its evolution in shape-memory-alloy single-crystals, in particular in CuAlNi. *Meccanica*, 40, 389–418, 2005.
- [MaM05] A. MAINIK and A. MIELKE. Existence results for energetic models for rate-independent systems. *Calc. Var. PDEs*, 22, 73–99, 2005.
- [Mie05] A. MIELKE. Evolution in rate-independent systems (Ch. 6). In C. Dafermos and E. Feireisl, editors, *Handbook of Differential Equations, Evolutionary Equations, vol. 2*, pages 461–559. Elsevier B.V., Amsterdam, 2005.
- [Mie07] A. MIELKE. A model for temperature-induced phase transformations in finite-strain elasticity. *IMA J. Applied Math.*, 2007. In press.
- [MiR07] A. MIELKE and R. ROSSI. Existence and uniqueness results for a class of rate-independent hysteresis problems. *M³AS Math. Models Methods Appl. Sci.*, 17, 81–123, 2007.
- [MiT04] A. MIELKE and F. THEIL. On rate-independent hysteresis models. *Nonl. Diff. Eqns. Appl. (NoDEA)*, 11, 151–189, 2004. (Accepted July 2001).
- [MTL02] A. MIELKE, F. THEIL, and V. I. LEVITAS. A variational formulation of rate-independent phase transformations using an extremum principle. *Arch. Rational Mech. Anal.*, 162, 137–177, 2002.
- [SMZ98] A. SOUZA, E. MAMIYA, and N. ZOUAIN. Three-dimensional model for solids undergoing stress-induced phase transformations. *Europ. J. Mech., A/Solids*, 17, 789–806, 1998.