Optimization of porous materials for thermochemical storage of heat

Jochen Jänchen, Dietrich Ackermann, Eveline Weiler, Helmut Stach, Udo Hellwig

1. Introduction

Increasing interest in the application of the thermochemical storage or adsorption heat pumps for utilization of industrial waste heat and solar heat stimulated several experimental and theoretical studies on short and long term heat storage (Tchernev, 2001, Mittelbach et al., 2000, Hauer et al., 1999) as well as heat driven heat pumps (Meunier, 1986, Dieng, and Wang, 2001). However, less attention was paid to the properties of the porous materials such as common zeolites, silica gels or aluminosilicates which are mainly designed for catalysis and adsorption technologies but are not optimized for thermochemical heat storage applications.

In recent years some new storage materials were suggested and characterized such as the so called composite adsorbents (Levitskij et al., 1996, Jänchen et al., 2000) which have considerable high storage densities, a low charging temperature but their temperature lift is limited. Very recently (Jänchen, et al., 2002) we suggested the introduction of the AlPO_4 's for heat storage and heat transformation purposes. AlPO_4 's are zeolites-like microporous materials, which are mildly hydrophilic and may have the potential to close the gap between silica gels and zeolites in respect to the optimization of the adsorption strength of the water and the ability to be desorbed at mild conditions. Those microporous aluminophosphates can be modified by incorporation of some silicon into the lattice to tailor their adsorption properties with respect to the water adsorption/desorption properties.

The aim of this paper is to characterize the state of the art of the optimization of those new thermochemical storage materials, based on recent results, as an starting point for a continuation of the this project.

2. Experimental section

The materials used were new commercial low-silica zeolites, LiLSX and NaLSX (Tricat GmbH, Bitterfeld, Germany), own synthesis products of AlPO_4 -5, AlPO_4 -17, AlPO_4 -18 and SAPO-34 as well as the with CaCl_2 impregnated silica gel, attapulgite and activated carbon, respectively, with different pore size distributions.

The micro-, meso- and macroporous materials (microporous active carbon, two types of silica gel with mesopores (1) and macropores (2) and attapulgite with small macropores or big mesopores) were impregnated (in all cases) with 30% CaCl_2 . The salt was mainly accommodated in the pores. For the TG-experiments a LiNaX zeolite was used which was obtained by a Li-ion exchange of the Na-form of a commercial available X-zeolite (from CWK, Bad Köstritz, Germany).

Thermogravimetry (TG), differential scanning calorimetry (DSC) and the measurements of water isotherms were applied to compare the adsorption- and desorption properties of the different kinds of porous storage materials. The TG and DSC measurements were performed on a SETARAM TG-DSC 111 equipment with a heating rate of 5 K/min to a temperature of 673 K in a nitrogen stream of 1 L/h. Prior to the desorption experiment the water was adsorbed "off-line" in a desiccator at a relative pressure of 0.3 at room temperature overnight. Then the samples were transferred into the apparatus. The sorption isotherms were measured gravimetrically at 313 K with a home-made McBain quartz spring balance equipped with MKS Baratron pressure sensors (10^{-3} -1000 mbar). The sensitivity of the quartz spring amounts to 4 mg/mm. The expansion of the spring was measured using a kathetometer with a resolution of 0.01 mm. Before application, the samples (150-200 mg) were calcined in high vacuum ($<10^{-5}$ mbar) at 573 K (zeolitic materials) and 523 K (impregnated material) for 2-3 h.

Figure 1: Scheme of the 1.5 L thermochemical storage unit for 1 kg material.

Figure 2: Picture of the 1.5 L thermochemical storage unit for 1 kg material, the arrangement of the unit parts corresponds with the scheme in Figure 1.

A storage unit with a volume of about 1.5 L was used for the tests on a larger scale (see Figures 1 and 2). It consists of an adsorber (storage, center upper part in Figures 1 and 2) filled with approximately 1 kg of storage material and equipped with a heat exchanger. The heat exchanger of the storage is connected to a thermostat/pump for heat transfer in charging and discharging mode. The storage is connected with an evaporator (for discharging), a condenser with chiller for charging (desorption of water) and a vacuum pump. A diaphragm vacuum pump between the exit of the storage on top the condenser and the entry on bottom support the water vapour stream storage-condenser during charging. The set-up is equipped with pressure sensors, thermocouples and data acquisition. The heat during discharging of the thermochemical storage was transferred via heat exchanger into a water reservoir of 7 L volume. The maximum charging temperature amounts to 473 K. The minimum temperature in the condenser was 274 K. For discharging of the storage the temperature of the evaporator was kept at about 293 K.

3. Results and Discussion

3.1 Investigation of the adsorption properties of the microporous and mesoporous storage materials

In the following part the results of the physico-chemical characterization of the adsorption behaviour of water in microporous aluminophosphates are discussed and compared with zeolites and mesoporous materials.

Figure 3: Mass loss in a nitrogen flow between 300 and 670 K for LiNaX, SAPO-34, $\text{AlPO}_4\text{-18}$ and $\text{AlPO}_4\text{-17}$ (from top to bottom).

Figure 3 shows the TG profiles for the desorption of water from LiNaX, as an example of a common zeolite with a high storage density and a high temperature lift, and the microporous aluminophosphates $\text{AlPO}_4\text{-17}$, $\text{AlPO}_4\text{-18}$ and the SAPO-34. As can be seen, at about 400 K the main part of the water is removed from the AlPO_4 and SAPO samples different to the zeolite. The first derivative of the curves shows that the main part of the water from $\text{AlPO}_4\text{-5}$ is desorbed at about 370 K, from $\text{AlPO}_4\text{-17}$ at 380 K and from $\text{AlPO}_4\text{-18}$ at about 390 K. Incorporation of Si into the AlPO_4 -structure increases the maximum of the

desorption curve to about 400 K (SAPO-34) and the shape of the curve becomes more similar to the X zeolite. For the LiNaX the main peak is shifted to about 450 K and it takes another 200 K to achieve complete desorption. So, step by step modification of the molecular sieves as storage material seems to be possible to optimize their desorption properties with respect to the temperature level available for the charging of the storage.

The position of the water isotherms of the low silica X zeolites on one hand and the SAPO-34 on the other hand support the findings given above (see Figure 4). The isotherms of LiLSX and NaLSX are, compared to the SAPO, shifted by two orders of magnitude towards lower equilibrium pressure. Also the shape of the isotherm, which rise more steeply between 3-5 mbar due to a hydration of the SAPO (see Jänchen et al., 1993), differs from the common zeolites. Accordingly, the differential molar heats of sorption decreases from LiLSX (100-70 kJ/mol) to SAPO-34 (90-65 kJ/mol) and finally to the CaCl_2 /attapulgite system (70-50 kJ/mol water) significantly.

Figure 4: Adsorption isotherms of water at 313 K for LiLSX, NaLSX and SAPO-34 (molecular sieves, solid lines) as well as activated carbon/ CaCl_2 and the CaCl_2 impregnated attapulgite (dashed lines), from left to right.

Further, Figure 4 compares the isotherms of the zeolite-like materials with those of the impregnated active carbon and the attapulgite. Whereas the isotherm of the hydration of the CaCl_2 in the microporous activated carbon is comparable with the hydration of the SAPO, the CaCl_2 /attapulgite isotherm is again shifted towards higher equilibrium pressure in accordance with the decreasing heat of sorption. Obviously, there is an influence of the pore architecture on the hydration process of the hygroscopic salt. To discuss this phenomenon in more detail Figure 5 and Table 1 summarize the results of the TG/DSC measurements for the impregnated storage materials with different pore size distributions.

Material	Kind of porosity of the host	Sorbed amount in g/g	Q_{int} in kJ/mol	ρ_Q in Wh/g
Active carbon/ CaCl_2	microporous	0.385	53.4	0.317
Silica gel 1/ CaCl_2	mesoporous	0.395	50.6	0.299
Attapulgite/ CaCl_2	small macropores	0.395	48.7	0.297
Silica gel 2/ CaCl_2	macroporous	0.490	50.7	0.382

Table 1: Results of the TG/DSC measurements: sorbed amounts of water, integral molar heats of sorption of the water and energy densities for impregnated materials with different pore size distribution

Figure 5: Adsorption isotherms of water at 313 K for activated carbon/ CaCl_2 (filled points desorption), silica gel 1/ CaCl_2 and the CaCl_2 impregnated attapulgite (from left to right).

As can be seen the shape and position of the isotherms, the integral molar heats of sorption (hydration) and the storage densities are influenced by the pore architecture of the hosting material. Whereas in the meso- and macroporous supports the pores are big enough (20-60 nm in diameter) to form one after the other the dihydrate (first step at 0.1 g/g in Figure 5), the tetrahydrate (step at 0.2 g/g) and at higher equilibrium pressures the hexahydrate (see Jänchen et al., 2000). However, the isotherm of the active carbon do not show a stepwise course in accordance with XRD measurements and has a hysteresis loop different to the other materials (for $a < 0.1$ g/g). In the XRD no diffraction pattern for any hydrate can be observed different to the other materials with bigger pores. Obviously, no defined hydrates can be created in the small micropores with a diameter of < 4 nm.

3.2 Investigation of the micro- and mesoporous materials in the lab-scaled storage

Material	Desorption temperature in K	(Ad)sorbed amount water in kg/kg	Energy density in Wh/kg	Max. temperature in the storage in K
LiLSX	473	0.24	225	380
NaLSX	473	0.23	185	370
SAPO	373, 423	0.23	154	345
Active carb./ CaCl_2	393	0.223	161	350
Attapulgite/ CaCl_2	393	0.18	177	336
Silica gel	393	0.18	123	335

Table 2: Desorption temperatures, adsorbed amounts of adsorbed water, energy densities and maximum temperature in the storage for zeolites, SAPO, pure silica gel and impregnated materials

Table 2 and Figure 6 show the results for selected micro- and mesoporous storage materials obtained by measurements with the lab-scaled storage. As can be seen the new low silica X-type zeolite (in the Li- and Na form) gives the highest values for the adsorbed amounts of water, the storage densities and the maximum temperature which could be achieved in the storage (see also Figure 6). In the

case of the SAPO, the impregnated microporous activated carbon and the mesoporous materials (common silica gel and an impregnated attapulgite) the desorption (charging) temperature can be lower as for LSX but the maximum temperature in the storage in discharging mode is lower as well. As it is known those mesoporous materials are suitable for application of solar heat (Mittelbach et al. 2000) but with a limited temperature lift. However, Figure 6 shows that those limits are less pronounced for the SAPO. The temperature profile of the latter is between the zeolites and the mesoporous materials. Next to the SAPO follows the impregnated activated carbon followed by the silica gel at the lowest temperature. The flat course of the temperature profile of the SAPO from the beginning at a medium temperature in the storage is in accordance with the thermodynamic behaviour discussed above.

Figure 6: Temperature profiles of different storage materials inside the storage vs. time: LiLSX, NaLSX, SAPO, activated carbon/ CaCl_2 and pure silica gel (from top to bottom).

Because the SAPO molecular sieves are still expensive in their production and the CaCl_2 -impregnated materials show sometimes instability we continue the research work by other techniques of zeolite modification and by application of hygroscopic salt hydrates of more stable acids.

4. Conclusions

It was shown that zeolites of different types have a higher temperature lift during discharging of a thermochemical storage. However, the charging temperature of those materials exceed 473 K which is practically not easy to achieve by common solar collectors. Silica gel or impregnated mesoporous materials show a high storage density and need a lower charging temperature, about 393 K, but the temperature lift is low. The impregnation of porous hosts with different pore architecture results in different storage properties.

Water from microporous aluminophosphates and silicoaluminophosphates can be desorbed almost completely at temperatures < 420 K. The storage density is comparable with zeolites and the differential molar heats of adsorption of water are between those of zeolites and impregnated storage materials. The results of the measurements in the lab-scaled storage show that the temperature lift is in between

as well. Thus, it can be expected that microporous SAPO's and AlPO_4 's have the potential of zeolite like storage properties, however, with a lower charging temperature and, hence, meet the conditions for solar application. Application of other methods of modification are in progress to reduce production costs and to increase chemical stability of the new thermochemical storage materials.

Acknowledgement

We thank W. Brösicke (FHTW Berlin) for his kind support of this research work in recent years. The supply of the LSX and SAPO samples by Dr. H. Toufar (Tricat GmbH, Bitterfeld, Germany) and the financial support of this work by the Bundesministerium für Wirtschaft und Arbeit (BMWA), grant number 0329525 F, is acknowledged.

References

- Hauer, A., Engelhardt, M. (1999) *Stability of Zeolites in Open Cycle Sorption Processes*, in Proceedings of the 1999 International Heat Pump Conference, Munich, Germany, March 24-26, 1999, pp 269-273.
- Dieng, A.O. and Wang, R.Z. (2001), *Literature review on solar adsorption technologies for ice-making and air-conditioning purposes and recent developments in solar technology*, Renewable & Sustainable Energy Reviews, Vol. 5, pp. 313-342.
- Jänchen, J., Peeters, M.P.J., de Haan, J.W., van de Ven, J.M., van Hooff, J.H.C., Girmus, I., Lohse, U. (1993) *Adsorption Calorimetric Measurements and ^{27}Al DOR NMR Studies on the Molecular Sieve AlPO_4* , J. Phys. Chem. Vol. 97, pp. 12042-12046.
- Jänchen, J., Grimm, A., Stach, H. (2000) *Physico-chemical studies of porous materials for thermochemical storage of heat*, Proceedings of the 5th Workshop IEA, ECESIA Annex 10, April 12-13 2000, Tsu, Mie, Japan, <http://www.fskab.com/annex10/workshops>.
- J. Jänchen, D. Ackermann, H. Stach, (2002) *Adsorption Properties of Aluminophosphate Molecular Sieves - Potential Applications for Low Temperature Heat Utilization*, in R.Z. Wang (Ed), Proceedings of the Int. Sorption Heat Pump Conference, Shanghai, P.R. China, September 24-27, 2002 pp635-638.
- Meunier, F. (1986) *Discussion of thermodynamic analysis of a solar zeolites system*, J. Solar Energy Engin. Vol. 108, p. 257.
- Mittelbach, W., Núñez, T., Luginsland, F., Henning, H-M. (2000) *Solid sorption thermal energy storage for solar heating systems*, in Brenner, M. and Hahne, E.W.P. (Eds.), *Proceedings of the Terrastock 2000 Conference*, Stuttgart, Germany, August 28 - September 1, 2000, pp 415-420.
- Levitskij, E.A., Aristov, Yu.I., Tokarev, M.M. and Parmon, V.N. (1996), *Chemical heat accumulators: a new approach to accumulating low potential heat*, Solar Energy and Solar Cells 44, 219-235.
- Lok, B.M., Messina, C.A., Gajek, R.T., Flanigen, E.M. (1984) *US Patent No. 4440871*.
- Tchernev, D.I. (2001) *Natural zeolites in solar energy, heating, cooling, and energy storage*, in: Bish, D.L. and Ming, D.W. (Eds.) *Natural Zeolites: Occurance, Properties, Applications, Reviews in Mineralogy & Geochemistry*, Vol. 45, pp. 589-617.
- Wilson, S.T, S., Lok, B.M., Flanigen, E.M., Plains, W. (1982) *US Patent No. 4310440*.

Affiliations

Dr. rer. nat. Jochen Jänchen
Technische Fachhochschule Wildau
Ingenieurwesen/Wirtschaftsingenieurwesen

Dr. rer. nat. Dietrich Ackermann
Technische Fachhochschule Wildau
Ingenieurwesen/Wirtschaftsingenieurwesen

F-Ing. Eveline Weiler
Technische Fachhochschule Wildau
Ingenieurwesen/Wirtschaftsingenieurwesen

Prof. Dr. sc. nat. Helmut Stach
ZeoSys GmbH
Volmerstr. 13, 12489 Berlin-Adlershof

Prof. Dr. Ing. Udo Hellwig
Technische Fachhochschule Wildau
Tel. +49 3375 508-170
hellwigu@vt.tfh-wildau.de